

MA 10: Poster I

Time: Tuesday 10:45–13:45

Location: Poster A

MA 10.1 Tue 10:45 Poster A

Theoretical study of the influence of Ni-bridge-Ni angles on magnetic anisotropy and exchange — ●CLAUDIA LOOSE and JENS KORTUS — TU-Bergakademie Freiberg, Institut für Theoretical Physics, Leipziger Str. 23, 09599 Freiberg, Germany

We studied the effect of distortions in the Ni-bridge-Ni angles of 5 small Ni-dimers by means of density functional theory calculations. In three cases we observed a decrease of the magnetic exchange coupling constant J with increasing magnetic anisotropy D . However, one of the Ni-dimers showed the opposite behaviour. The last discussed complex displays an abrupt change from easy-axis to easy-plane as soon as one leaves the experimental geometry.

These results suggest that the development of simple guiding rules for rational design of magnetic anisotropy, similar to the well known Goodenough-Kanamori rules, may be difficult and a more detailed description based on electronic structure information may be required.

MA 10.2 Tue 10:45 Poster A

Magnetic anisotropy of paramagnetic porphyrin molecules on non-magnetic surfaces: an angle-dependent XMCD investigation — ●MATTHIAS BERNIEN¹, JORGE MIGUEL¹, WOLFGANG KUCH¹, ADRIAN D. WARD CHERRIER², CARSTEN TIEG², CLAUDIA WEIS³, CAROLIN ANTONIAK³, DIETGER BOVENSCHEN³, and HEIKO WENDE³ — ¹Institut für Experimentalphysik, Freie Universität Berlin, Arnimallee 14, 14195 Berlin — ²ESRF, BP 220, F-38043 Grenoble Cedex, France — ³AG Wende and Center for Nanointegration (CeNIDE), Universität Duisburg-Essen, Lotharstrasse 1, 47048 Duisburg

Metal complexes on surfaces are a topic of intensive scientific investigations since the properties of their central metal ion, determined by the adjacent ligands, can be widely tuned by the chemical design of the molecule. Here we report on the electronic structure and the magnetic properties of paramagnetic Fe and Co octaethylporphyrin molecules adsorbed on non-magnetic Cu(100) and oxygen-covered ($\sqrt{2} \times \sqrt{2}$)R45° O/Cu(100) surfaces. The magnetic moments of the metal centers of the molecules are aligned by an external magnetic field of 5 T at a temperature of 8 K. The magnetic anisotropy of the metal centers is probed by XMCD measurements along the easy and hard magnetization direction. For Fe porphyrin molecules on the bare Cu(100) substrate a negligible magnetic anisotropy is found. In contrast, a huge magnetic anisotropy of the Fe ion can be obtained by placing half a monolayer of atomic oxygen between the molecules and the Cu(100) surface. This work has been supported by DFG (Sfb 658 and Sfb 491) and ESRF (HE 2700).

MA 10.3 Tue 10:45 Poster A

Electron spin dynamics in novel binuclear Mn molecular complexes — ●Y. KRUPSKAYA¹, R. ZARIPOV², E. VAVILOVA^{1,2}, A. PARAMESWARAN¹, V. MILUYKOV³, I. BEZKISHKO³, D. KRIVOLAPOV³, O. KATAEVA³, O. SINYASHIN³, E. HEY-HAWKINS⁴, V. VORONOVA², K. SALIKHOV², R. KLINGELER¹, V. KATAEV¹, and B. BÜCHNER¹ — ¹IFW Dresden, Dresden, Germany — ²Zavoisky Physical-Technical Institute of the RAS, Kazan, Russia — ³A.E. Arbutov Institute of Organic and Physical Chemistry of the RAS, Kazan, Russia — ⁴Institute of Inorganic Chemistry, Leipzig University, Leipzig, Germany

We present a study of electron spin dynamics in novel Mn-dimer molecular complexes which show strong dependence of the electron density distribution at the Mn sites on the ligand surrounding. Using the pulsed electron spin resonance (ESR) technique we have detected electron spin echo and determined spin-lattice relaxation (T_1) and phase-coherence (T_2) times which systematically depend on the ligand type. Interestingly, we observe an electron spin echo envelope modulation (ESEEM) associated with the coupling of the Mn electron spins to nearby proton moments. Moreover, we show that the spin-relaxation times can be substantially increased by reducing intermolecular interactions, for instance, by dissolving the crystals in a liquid media.

MA 10.4 Tue 10:45 Poster A

Incoherent Slow Magnetisation Dynamics in the Giant Kerpplerat Molecule Fe₃₀Mo₇₂ — ●T. DELLMANN¹, H.-H. KLAUSS¹, J. SCHNACK², and B. BÜCHNER³ — ¹Institut für Festkörperphysik, TU Dresden — ²Fakultät für Physik, Univ. Bielefeld — ³Leibniz-Institut für Festkörper- und Werkstofforschung Dresden

In the geometrically frustrated polyoxomolybdate nanomolecule Fe₃₀Mo₇₂ a distinct slowing down of the magnetisation dynamics is observed at temperatures of about 5K depending on the observation method [1, 2]. These dynamics still persist at very low temperatures down to 20 mK as shown by local probe techniques. Furthermore, no magnetisation steps could be found in the field dependent magnetisation at these temperatures as predicted by the quantum rotational band model [3].

We present recent low temperature ac-susceptibility results for different frequencies (200 Hz < f < 10 kHz) and external fields (0 < B < 2 T) and discuss them in comparison with results from μ^+ SR, NMR and ⁵⁷Fe moessbauer spectroscopy. The origin of decoherence at lowest temperatures is focussed in this discussion.

[1] Chr. Schröder et al., Phys.Rev.B 77, 224409 (2008)

[2] J. Lago et al., Phys.Rev.B 76, 064432 (2007)

[3] J. Schnack et al., Europhys. Lett., 56 (6), pp. 863-869 (2001)

MA 10.5 Tue 10:45 Poster A

High-field measurements of a spin-frustrated trinuclear copper (II) complex — ●WOLFGANG KROENER¹, AKSANA ZHARKOUSKAYA², EIKE T. SPIELBERG², DANIEL PLAUL², KLAUS GIEB¹, WINFRIED PLASS², and PAUL MÜLLER¹ — ¹Department of Physics and Interdisciplinary Center for Molecular Materials (ICMM), Universität Erlangen-Nürnberg, Germany — ²Institut für Anorganische und Allgemeine Chemie, Universität Jena, Germany

We present magnetic measurements of a trinuclear copper II complex based on triaminoguanidin (TAG): [Cu₃(bipy)₃(^HTAG)](ClO₄). A home-made micro-Hall-bar magnetometer and a commercial SQUID magnetometer were used to perform angle-resolved single crystal measurements. As the triangular structure of the complex suggests, we can conclude from our measurements, that we deal with a spin-frustrated system. Following a proposal of Trif et al.¹ we investigated the magnetization under high electric fields.

¹ M. Trif, F. Troiani, D. Stepanenko, D. Loss, Phys. Rev. Lett. 101, 217201 (2008).

MA 10.6 Tue 10:45 Poster A

Reinvestigation of the electronic and magnetic structure of the ferric star — ●DANIEL TAUBITZ¹, KARSTEN KUEPPER², ROLF SAALFRANK³, ANDREAS SCHEURER³, STEFAN SPERNER³, JÜRGEN SCHNACK⁴, and MANFRED NEUMANN¹ — ¹Department of Physics, University of Osnabrück, Barbarastrasse 7, D-49069 Osnabrück, Germany — ²Department of Solid State Physics, University of Ulm, Albert-Einstein-Allee 11, D-89069 Ulm, Germany — ³Institute for organic chemistry, Universität Erlangen-Nürnberg, Henkestr. 42, 91054, Erlangen, Germany — ⁴Department of Physics, University of Bielefeld, Universitätsstr. 25, D-33615 Bielefeld

Large polynuclear complexes which contain transition metal and/or rare earth metal ions are of current interest due to their tunable magnetic properties and the possibility to act as single molecule magnets (SMM). The use of SMMs for information technology (e.g. molecular memory arrays) is a main target in the field of molecular spintronics. Simplest inorganic systems, that show SMM behaviour like for example the ferric star Fe^{III}[Fe^{III}(L¹)₂]₃ have attracted much interest, since they can be investigated as model systems.

We investigated the ferric star with different X-ray spectroscopic techniques. The experimental results obtained by different groups using different methods will be compared and discussed.

MA 10.7 Tue 10:45 Poster A

Accuracy of the DMRG method applied to the antiferromagnetic Heisenberg icosidodecahedron — ●JÖRG UMMETHUM and JÜRGEN SCHNACK — Universität Bielefeld, Fakultät für Physik, Postfach 100131, D-33501 Bielefeld

Geometrically frustrated spin systems show a variety of fascinating properties like magnetization jumps or an enhanced magnetocaloric effect. There are many methods to study such systems like exact diagonalization, quantum Monte Carlo, or DMRG. Exact diagonalization is limited to rather small systems and quantum Monte Carlo suffers from the so-called negative sign problem. The DMRG method [1] is in principle free of such limitations but the accuracy is rather limited for systems with more than one dimension.

We present results of our DMRG studies of the antiferromagnetic Heisenberg icosidodecahedron and focus on the lowest energy levels in subspaces of total magnetic quantum number which form so-called rotational bands for many antiferromagnetic spin systems [2]. The accuracy of the results and possibilities to improve it, like different orderings of the spins, are discussed.

- [1] S. R. White, Phys. Rev. B **48**, 10345 (1993)
 [2] J. Schnack and M. Luban, Phys. Rev. B **63**, 014418 (2000)

MA 10.8 Tue 10:45 Poster A

DFT Studies Of A Magnetic Heptanuclear High-Spin Complex — ●STEFAN LEIDING¹, ANDREI POSTNIKOV², JÜRGEN SCHNACK¹, and DIRK ANDRAE^{1,3} — ¹Bielefeld University, Germany — ²Paul Verlaine University Metz, France — ³Freie Universität Berlin, Germany

The synthesis of molecular magnets has undergone rapid progress in recent years, therefore the ability to tune the couplings between the spins of individual transition metal atoms by controlled attachment of molecular ligands is examined using spin-dependent density functional theory. $\{[(\text{talen}^{\text{t-Bu}_2})\text{-}\{\text{Mn}^{\text{III}}(\text{solV})_n\}_3]_2\{\text{Fe}^{\text{III}}(\text{CN})_6\}\}^{3+}$ is a heptanuclear complex built via molecular recognition from three building blocks: two trinuclear manganese triplesalen units and one hexacyanometallate. In order to investigate the geometric and electronic effects on ferromagnetic coupling via the spin-polarization mechanism (well established in organic chemistry), we applied this mechanism to transition metal complexes. First of all we focus on much smaller fragments of the heptanuclear complex, e.g., the triplesalen ligand with three Mn^{III} centers and the $[(\text{N,N}'\text{-ethylenebis}(\text{salicylaldehyde}))\text{Mn}^{\text{III}}(\text{H}_2\text{O})_2]^+$ which contains only a single Mn^{III} ion. The influence of the ligand folding in these complexes causes a change in the orientation of the magnetic orbitals and in the spin-polarizations. These properties are examined by Kohn-Sham DFT calculations with the SIESTA and the TURBOMOLE programs.

MA 10.9 Tue 10:45 Poster A

Magnetic coupling of Co porphyrin molecules to ferromagnetic substrates — ●FELIX HERMANN, ALEXANDER KRÜGER, MATTHIAS BERNIEN, JORGE MIGUEL, and WOLFGANG KUCH — Freie Universität Berlin, Arnimallee 14, 14195 Berlin, Germany

Metalorganic compounds are promising candidates for spintronic devices. In this context, the interaction of the central transition metal ion of Fe-octaethyl-porphyrin molecules with underlying ferromagnetic substrates has been studied and found that it can be changed from parallel to antiparallel [1].

Here, we report on X-ray absorption spectroscopy (XAS) measurements of submonolayers of Co-octaethyl-porphyrin on bare and oxygen-covered Ni films grown on Cu(001). By means of angle-dependent XAS measurements at the N K-edge, a parallel orientation of the quasi-planar molecule is found with respect to the surface.

The Co $L_{3,2}$ XAS and XMCD spectra display significant differences for the two substrates. Angle-dependent spectral changes are explained by the distinct contributions of the individual Co 3d orbitals. The modification of the Co oxidation state by the adsorption on the two substrates is discussed. XMCD investigations yield a ferromagnetic coupling at room temperature between the Ni substrate and the Co ion only in the case of the bare metal surface. From the temperature dependence of the Co-XMCD signal, the magnetic coupling energy is evaluated.

This work is supported by the DFG (Sfb 658).

- [1] M. Bernien et al., Phys. Rev. Lett. **102**, 047202 (2009)

MA 10.10 Tue 10:45 Poster A

Stability of Mn_6Cr single-molecule-magnets adsorbed on surfaces: The influence of X-ray exposure, layer thickness, choice of substrate and counterions — ●ANDREAS HELMSTEDT¹, AARON GRYZIA¹, SEBASTIAN STEPELER¹, NORBERT MÜLLER¹, MARC D. SACHER¹, ULRICH HEINZMANN¹, VERONIKA HÖKE², THORSTEN GLASER², MIKHAIL FONIN³, and ULRICH RÜDIGER³ — ¹Fak. f. Physik, Uni Bielefeld — ²Fak. f. Chemie, Uni Bielefeld — ³Fak. f. Physik, Uni Konstanz

The single-molecule-magnet (SMM) Mn_6Cr consists of three main components: Two bowl-shaped Mn_3 -salen complexes are bridged by a complex containing one Cr atom. Three counterions are coupled to the triply charged SMM to ensure charge neutrality. Mn_6Cr -SMM have a low stability against X-ray exposure, which adversely affects a study of the electronic properties by X-ray absorption- and photoelectron spectroscopy. With increasing exposure time, the spectral

features of trivalent Mn representing intact molecules disappear while Mn(II)-typical features increase. This degradation process and its dependence on the photon flux, the substrate and the SMM concentration were observed during beamtimes at BESSY II and MAXLAB III. The rate of degradation shows also a strong dependence on the choice of counterions. The chosen preparation method allows the adsorption of Mn_6Cr -SMM with varying layer thickness on various substrates. This study reveals an influence of the substrate and the molecule layer thickness on the initial electronic state of the adsorbed molecule layer, i.e. the molecules seem to degrade already during the adsorption process.

MA 10.11 Tue 10:45 Poster A

Homogenous adsorption of Mn_6Cr single-molecule-magnets on substrates — ●PETER KOOP¹, AARON GRYZIA¹, ANDREAS HELMSTEDT¹, WIEBKE HACHMANN¹, ARMIN BRECHLING¹, MARC SACHER¹, ULRICH HEINZMANN¹, VERONIKA HÖKE², and THORSTEN GLASER² — ¹Molecular and Surface Physics, Bielefeld University — ²Anorganic Chemistry I, Bielefeld University

Mn_6Cr is a single-molecule-magnet (SMM) consisting of two bowl-shaped compounds, each containing three Mn-atoms. These compounds are bound together by a Cr-complex. For charge neutrality, counterions have to be coupled to the SMM. Investigation of separated SMM, the molecule-substrate interaction and/or possible future applications e.g. data storage, requires preparation of monolayers or thin films. This preparation is done by solving Mn_6Cr in methanol, and dropping few μl of the solution onto a 9x9 mm sized substrate. Depending on the choice of substrate Au, SiO_2 (native Oxide, 50 nm Oxide), HOPG, Ru, Mn_6Cr concentration, the angle of the sample while being prepared and the amount of applied solution Mn_6Cr yields strongly varying kinds of assembly. On the one hand, clusters emerge in the solution just a moment before the solvent dries, depending on the concentration of Mn_6Cr in the solution. On the other hand the lateral distribution of the SMM is correlated with the droplet-size, the angle of the sample during preparation and the counterions, e.g. lactate anions cause Mn_6Cr to create membranes. The samples have been investigated by means of optical microscopy, SEM, surface profilometry and AFM.

MA 10.12 Tue 10:45 Poster A

Single molecule magnets on surfaces: recent advances and future perspectives — SÖNKE VOSS¹, ●SAMUEL BOUVRON¹, ULRICH RÜDIGER¹, MIKHAIL FONIN¹, MICHAEL BURGERT², and ULRICH GROTH² — ¹Fachbereich Physik, Universität Konstanz, 78467 Konstanz — ²Fachbereich Chemie, Universität Konstanz, 78467 Konstanz

In recent years, single molecule magnets (SMMs) have attracted much attention due to their unique properties such as quantum tunneling of magnetization (QTM) and hysteresis of pure molecular origin [1], making these materials potential candidates for future applications in ultra-high density data storage devices. Only very recently first experiments indicating the conservation of magnetic properties of SMM clusters upon surface deposition have been reported boosting the investigation of SMM monolayers [2].

We present an overview of the latest achievements in the investigation of Mn_{12} monolayers as well as the individual molecules by means of scanning probe techniques, synchrotron radiation based techniques, and magnetization measurements. In particular, novel approaches towards the assembly of Mn_{12} SMMs on substrates suited for advanced studies or possible applications are highlighted.

This work was supported by DFG through SFB 767 (TP C5).

- [1] D. Gatteschi and R. Sessoli, Angew. Chem. Int. Ed. **42**, 268 (2003).
 [2] M. Mannini et al., Nature Mater. **8**, 194 (2009).

MA 10.13 Tue 10:45 Poster A

Properties of TiO_2/Fe composites investigated by ab initio calculations — ●ANNA GRÜNEBOHM, HEIKE C. HERPER, and PETER ENTEL — Fakultät für Physik, Universität Duisburg-Essen

Multiferroic materials offer interesting new applications through the coupling or coexistence of two order parameters - particularly ferroelectricity and ferromagnetism. While ferromagnetism is mainly mediated by highly localized d - and f - electrons, conventional ferroelectricity is mediated by cation off-centering which is based on empty d -shells. Therefore, multicomponent systems are promising alternatives for high performance multiferroics [1]. In such composites, the ferroelectric and ferromagnetic phases are coupled through hybridization and strain effects at the interfaces. To get an insight into the interface properties of such systems, we do calculations within the projector augmented

wave method using VASP [2]. We investigate Fe/TiO₂ agglomerates as simple model systems in order to study fundamental properties of such interfaces. Although TiO₂ does not possess a ferroelectric phase, it offers a large polarizability and a magnetoelectric effect has been measured in Fe/TiO_{2-δ} films [3]. This means that TiO₂ interfaces possess similar properties as ferroelectrics. Until now little is known of the interface structure of TiO₂/Fe agglomerates. Hence, we present a systematic study of different layered systems as well as agglomerated nanoparticles.

[1] R. Ramesh and N. A. Spaldin, *Nat. Mater.* **6**, 21 (2007) [2] G. Kresse and J. Furthmüller, *Phys. Rev. B* **54**, 11169 (1996) [3] S. D. Yoon, *et al*, *Appl. Phys. Lett.* **92**, 042508 (2008)

MA 10.14 Tue 10:45 Poster A

Magnetism and ferroelectricity of Mn-doped BaTiO₃ thin films — ●YAO SHUAI, DANILO BÜRGER, SHENGQIANG ZHOU, MANFRED HELM, and HEIDEMARIE SCHMIDT — Forschungszentrum Dresden-Rossendorf e.V., Bautzner Landstraße 400, 01328 Dresden

Strained BaTiO₃ (BTO) thin films grown by pulsed-laser deposition (PLD) on SrTiO₃ substrates can result in a nearly 500 K larger ferroelectric transition temperature. The remanent polarization of strained BTO thin films is at least 250% higher than that in BTO single crystals [1]. We used PLD to grow Mn-doped BTO (BTMO) thin films on MgO, and c-plane sapphire substrates. For example, we observed XRD reflexes of (001)- and (100)-oriented domains on BTMO deposited on MgO and sapphire, indicating the BTMO films are polycrystalline. At room temperature the saturated magnetic moment of BTMO films with a thickness of 400nm on MgO substrates amounted to 8 emu/cm³, while that of the films deposited on c-sapphire was merely 1 emu/cm³ even at 5 K, resulting from a weak domain orientation due to the large lattice mismatch between BTMO and c-sapphire. A capacitance-voltage hysteresis behavior of BTMO films on Pt/c-sapphire has been probed under a driving voltage of 50 mV at 100 kHz, which can be ascribed to the nonlinear ferroelectric response [2]. The simultaneously observed magnetic and ferroelectric ordering proves the feasibility of multiferroic BTMO for novel device applications[3]. [1] K. J. Choi et al., *Science* **306** (2004) 1005. [2] M. Dawber et al., *Reviews of Modern Physics* **77** (2005) 1083. [3] R. Ramesh et al., *Nature Materials* **6** (2007) 21. (2007) 21.

MA 10.15 Tue 10:45 Poster A

Angle-dependent magnetotransport in Nickel thin films — ●M. ALTHAMMER, M. WAGNER, A. BRANDLMAIER, M. WEILER, S. GEPRÄGS, R. GROSS, and S.T.B. GOENNENWEIN — Walther-Meißner-Institut, Bayerische Akademie der Wissenschaften, Garching, Germany

Angle-dependent magnetoresistance (ADMR) measurements have proven to be a powerful tool to investigate magnetic anisotropy in ferromagnetic thin films [1]. We here apply the ADMR technique to polycrystalline Nickel thin films deposited via electron beam evaporation onto LiNbO₃, MgO and BaTiO₃ substrates. The 50 nm thick films were patterned into Hall-bar structures with optical lithography and etching or lift-off. In the ADMR measurements, the longitudinal and transverse resistance is recorded as a function of the orientation of the external magnetic field at constant field strength. In all samples investigated the strain in the Nickel thin film can be tuned in situ, either via temperature or an applied electric field. Due to magnetoelectric coupling the strain leads to a change in the magnetic anisotropy. We can quantitatively explain our data with basic magnetoelastic coupling theory, taking into account the thermal dependence of the lattice parameters of the respective substrate. Fitting the data by a single domain model allows to extract the magnetic anisotropy. We also discuss the external magnetic field and temperature dependence of the resistivity parameters. Financial Support by the DFG (SPP 1157 and GO 944/3) is gratefully acknowledged.

[1] W. Limmer *et al.*, *PRB* **74**, 205205 (2006)

MA 10.16 Tue 10:45 Poster A

Investigation of strain effects in epitaxial CaMnO₃ films by nonlinear optics — ●TIM GÜNTHER¹, SATADEEP BHATTACHARJEE², PHILIPPE GHOSEZ², ADRIAN DAVID³, WILFRID PRELLIER³, and MANFRED FIEBIG¹ — ¹HISKP, University of Bonn, Germany — ²University of Liege, Belgium — ³CRISMAT Laboratory, ENSICAEN, CNRS, France

The family of ABO₃ perovskite oxide compounds constitutes an important class of multifunctional materials. For CaMnO₃, a G-type antiferromagnetic insulator (T_N = 122 K), a weak Mn-driven ferroelectric instability at its equilibrium volume was recently predicted.

Furthermore this instability can be enhanced by strain engineering, driving CaMnO₃ towards multiferroicity.

Here optical second harmonic generation (SHG) was used for investigating CaMnO₃ films grown epitaxially with 2% tensile strain on (001)-LaAlO₃ substrates. The temperature dependence of the SHG signal indicates a phase transition at ≈ 20 K with an emergence of long range order that is not found in the bulk compound. SHG polarization analysis based on SHG selection rules allows to determine the origin of this novel phase. A variety of possible ferroelectric polarization directions was considered on the basis of a symmetry analysis. First results on SHG spectroscopy and domain imaging are reported. This work is supported by the EU-STREP MaCoMuFi.

MA 10.17 Tue 10:45 Poster A

First-principles study of ferroelectric domain walls in multiferroic bismuth ferrite — AXEL LUBK^{1,2}, ●SIBYLLE GEMMING³, and NICOLA SPALDIN² — ¹Institute of Physics, Technical University, D-01062 Germany. — ²Materials Department, University of California, Santa Barbara, California 93106-5050, USA. — ³Inst. Ion Beam Physics and Materials Research, FZ Dresden-Rossendorf, D-01314 Dresden, Germany.

The structural, electronic, and magnetic properties of the ferroelectric domain walls in multiferroic BiFeO₃ were studied by density-functional band-structure calculations. Domain walls in which the rotations of the oxygen octahedra do not change their phase when the polarization reorients are the most favorable and of these, the 109° domain wall centered around the BiO plane has the lowest energy. The 109° and 180° walls have a significant change in the component of their polarization perpendicular to the wall; the corresponding step in the electrostatic potential is consistent with a recent report of electrical conductivity at the domain walls. Finally, we show that changes in the Fe-O-Fe bond angles at the domain walls cause changes in the canting of the Fe magnetic moments which can enhance the local magnetization at the domain walls.

[1] Seidel et al., *Nature Mater* **8** (2009) 229; [2] Lubk et al., *Phys. Rev. B* **80** (2009) 104110.

MA 10.18 Tue 10:45 Poster A

Separation and magnetic-field dependence of contributions to the magnetically induced net polarization in multiferroic TbMn₂O₅ — ●NAËMI LEO¹, THOMAS LOTTERMOSER¹, DENNIS MEIER¹, ROMAN V. PISAREV², and MANFRED FIEBIG¹ — ¹HISKP, Universität Bonn — ²Ioffe Physical Technical Institute, Russian Academy of Sciences

Strong magnetoelectric coupling is expected in multiferroics in which the ferroelectric polarization is directly induced by the magnetic order. A particularly interesting magnetoelectric multiferroic is TbMn₂O₅, which shows a reversal of the spontaneous ferroelectric polarization *P* upon application of a magnetic field. Theoretical approaches predict two contributions to the net polarization directly linked to the magnetic order of the system.

The analysis of nonlinear spectra of TbMn₂O₅ measured by optical Second Harmonic Generation (SHG) reveals not only two but three distinct contributions P_1^{Mn} , P_2^{Mn} and P_3^{Tb} , whereas in pyroelectric measurements only the net polarization can be seen. It has been shown that the third contribution P_3^{Tb} is linked to the magnetic order of the Tb sublattice. Furthermore, spatial resolved measurements reveal additional domain structures at low temperatures.

Performing nonlinear optical measurements in an applied magnetic field reveals that the change of sign in the ferroelectric net polarization in TbMn₂O₅ is driven by an magnetoelectric interaction with the rare-earth order: $P(T, B) = P_1^{\text{Mn}}(T) - P_2^{\text{Mn}}(T, H) \pm P_3^{\text{Tb}}(T, H)$. This work was supported by the DFG through SFB 608.

MA 10.19 Tue 10:45 Poster A

Influence of doping on the lattice dynamics: Comparison of stoichiometric and mixed orthorhombic rare earth manganites RMnO₃ (R = Gd, Tb, Eu:Y) — ●S. ISSING¹, F. FUCHS¹, C. ZIEREIS¹, E. BATKE¹, A. PIMENOV¹, Y. VU. IVANOV², A. A. MUKHIN², and J. GEURTS¹ — ¹Physikalisches Institut, Universität Würzburg, Germany — ²General Physics Institute of the Russian Academy of Sciences, Moscow, Russia

Among the class of multiferroics, the orthorhombic manganites RMnO₃ are an excellent example for the intimate coupling of lattice and magnetic degrees of freedom. For a fine tuning of the magnetic properties the isovalent substitution of the R ion can be employed leading to a quasi-continuous increase of the orthorhombic crystalline

distortion and thus of the magnetic frustration responsible for multiferroicity. However the question of disorder induced by isovalent substitution needs to be addressed. Thus, employing Raman and FTIR spectroscopy, we studied the lattice dynamics of stoichiometric ($R = \text{Eu, Gd, Tb}$) as well as mixed RMnO_3 compounds ($\text{Eu}_{1-x}\text{Y}_x$ $0 \leq x \leq 0.5$ - covering the R ion radius from Eu to Tb) - to gain insight into the consequences of an isovalent partial substitution on the R-site. Our spectroscopic techniques give us sensitivity not only to symmetry properties but also to the involvement of different ion types within the unit cell. Our results clearly show that the MnO_6 -octahedra remain unaffected by disorder, making $\text{Eu}_{1-x}\text{Y}_x\text{MnO}_3$ an excellent model system for a quasi-continuous fine-tuning of the lattice properties relevant for the appearance of multiferroicity.

MA 10.20 Tue 10:45 Poster A

Spin-phonon coupling in multiferroic stoichiometric and mixed RMnO_3 compounds ($R = \text{Gd, Tb, Eu; Y}$) studied by Raman spectroscopy — ●S. ISSING¹, A. PIMENOV¹, Y. VU. IVANOV², A. A. MUKHIN², and J. GEURTS¹ — ¹Physikalisches Institut, Universität Würzburg, Germany — ²General Physics Institute of the Russian Academy of Sciences, Moscow, Russia

Spin-phonon coupling, manifesting itself as phonon softening in the temperature range of the magnetically ordered phases is investigated by temperature dependent polarized Raman spectroscopy. Stoichiometric ($R = \text{Eu, Gd, Tb}$) and mixed ($R = \text{Eu}_{1-x}\text{Y}_x$, $0 \leq x \leq 0.5$ - covering the R ion radius range of the stoichiometric compounds) multiferroic orthorhombic RMnO_3 are compared in the 10 - 300 K temperature range. The strength and temperature dependence of the phonon softening depend strongly on the mode symmetry showing the correlation of this effect with the magnetic interaction of the Mn^{3+} ions within the MnO_2 -plane leading to the strongest phonon renormalization for the in-plane symmetric stretching mode ($B_{2g}(1)$). Quantitative spin-phonon coupling constants for all investigated systems are derived showing the trend of weakend spin-phonon coupling for decreasing R ion radius. Strikingly, spin-phonon coupling is observed even for RMnO_3 compounds with an incommensurate magnetic structure of the Mn^{3+} spins, i.e. without long-scale magnetization. This underscores the role of phonons as a quasi-local probe.

MA 10.21 Tue 10:45 Poster A

Magnetic Structure of Multiferroic DyMnO_3 studied by Resonant Soft X-ray Scattering — ●ENRICO SCHIERLE, VICTOR SOLTWISCH, DETLEF SCHMITZ, RALF FEYERHERM, ANDREY MALJUK, FABIANO YOKAICHIYA, DIMITRI ARGYRIOU, and EUGEN WESCHKE — Helmholtz-Zentrum Berlin

In multiferroic DyMnO_3 , ferroelectricity is induced by a cycloidal magnetic structure of Mn-3d moments. However, it has been shown that ordering of Dy-4f moments strongly influences the ferroelectric properties of this compound. We examined the magnetic structure of Dy-4f moments by resonant magnetic X-ray scattering (RMXS) at the Dy-M_5 resonance in detail. As the main result, we show that over a large temperature range of the ferroelectric phase, Dy-4f moments form a magnetic cycloid of a chirality coupled to the direction of the electric polarization. This property can be exploited to map the ferroelectric domain structure at the crystal surface by RMXS.

MA 10.22 Tue 10:45 Poster A

Investigation of the triangular multiferroic order in CuCrO_2 by second harmonic generation — ●VERA CAROLUS¹, KENTA KIMURA², TSUYOSHI KIMURA², and MANFRED FIEBIG¹ — ¹Helmholtz-Institut für Strahlen- und Kernphysik, Nußallee 14-16, D-53115 Bonn — ²Devison of Materials Physics, Graduate School of Engineering Science, Osaka University, Toyonaka, Osaka 560-8531, Japan CuCrO_2 (space group $R\bar{3}m$) is a triangular lattice antiferromagnet with delafossite structure showing a modulated out-of-plane 120° spin order below $T_N = 23.6$ K. Because of the breaking of inversion symmetry by the magnetic order a magnetically induced electric polarisation with six different domains should exist.

Here we investigate the multiferroic order of CuCrO_2 by optical second-harmonic generation (SHG) spectroscopy. Although the value of spontaneous polarisation is about four orders of magnitude weaker than in a conventional ferroelectric, a clear SHG signal with a pronounced spectral and polarization dependence is obtained. This giant coupling to the SHG progress is not restricted to CuCrO_2 , but is also observed in MnWO_4 , TbMn_2O_5 and CuO . This points to electronic instead of ionic nature of the ferroelectric polarisation.

In SHG imaging experiments the topology of the multiferroic do-

main (and their manipulation) were investigated. Crystallographic and magnetic correlations between the six types of domains were revealed.

MA 10.23 Tue 10:45 Poster A

Magnetic structure in multiferroic pyroxenes: (Na, Li)FeSi₂O₆ — ●MAX BAUM¹, ALEXANDER KOMAREK¹, NAVID QURESHI¹, PETRA BECKER², LADISLAV BOHATÝ², MARTIN MEVEN³, ASTRID SCHNEIDEWIND³, PETER LINK³, MARIA FERNANDEZ-DIAZ⁴, PAUL STEFFENS⁴, and MARKUS BRADEN¹ — ¹II. Phys. Inst., Universität zu Köln, Zùlpicher Str. 77, 50937 Köln, Germany — ²Inst. für Geologie und Mineralogie, Universität zu Köln, Zùlpicher Str. 49b, 50674 Köln, Germany — ³Forschungsneutronenquelle Heinz Maier-Leibnitz (FRM II), Lichtenbergstr. 1, 85747 Garching, Germany — ⁴4 Institut Laue-Langevin, BP 156, 6 rue Jules Horowitz, 38042 Grenoble Cedex 9, France

(Na/Li)FeSi₂O₆ both exhibit multiferroic properties. In NaFeSi₂O₆ magnetic ordering is incommensurate with a temperature independent modulation $k=(0, 0.23, 0)$. The antiferromagnetic order occurs below 8K and additionally ferroelectric ordering below 6K. Polarized neutron diffraction shows that at this transition chiral magnetic components develop. Ferroelectric order in NaFeSi₂O₆ seems thus to arise from the inverse Dzyaloshinski-Moriya interaction. Similarly, magnetically driven ferroelectricity is detected in LiFeSi₂O₆ below 18K but only at applied magnetic field. In both these compounds the electric polarization can be strongly modified by magnetic fields. Our measurement on a single crystal reveals the Shubnikov group $P21/c'$. On the basis of the magnetic structure we calculated the toroidal moment for LiFeSi₂O₆: $T=-0.037\text{muB}/\text{Å}^2$. This is about ten times larger than in LiCoPO₄, the first compound where ferrotoroidicity was unambiguously observed.

MA 10.24 Tue 10:45 Poster A

Response of antiferromagnetic and ferrotoroidic domains in LiCoPO₄ to magnetic and electric fields — ●ANNE S. ZIMMEMANN¹, BAS B. VAN AKEN¹, JEAN-PIERRE RIVERA², HANS SCHMID², and MANFRED FIEBIG¹ — ¹HISKP, University of Bonn, Germany — ²Department of Inorganic, Analytical and Applied Chemistry, University of Geneva, Switzerland

Ferrotoroidicity denotes a fourth form of ferroic order with a spontaneous uniform alignment of magnetic vortices. Recently the observation of antiferromagnetic (AFM) domains coexisting with ferrotoroidic (FTO) domains in LiCoPO₄ was reported in second harmonic generation (SHG) experiments [1]. Controlled manipulation of these FTO domains would be the next step in demonstrating the ferroic nature of the toroidal state. This could be achieved by a toroidal field, e. g. crossed electric and magnetic fields.

Here we report on the behaviour of AFM and FTO domains in external magnetic, electric, and toroidal fields. The domain structure in zero-field cooling and field-cooling experiments was investigated by SHG. Experiments showed that a magnetic field of around 5 T along the x axis changes and pins the domains. Furthermore indications for an additional phase transition were observed. Toroidal poling is thus not possible. Therefore a setup for smaller magnetic and higher electric fields was developed. - Work supported by the SFB 608.

[1] B. B. Van Aken et. al., Nature 449, 702 (2007)

MA 10.25 Tue 10:45 Poster A

Magneto-optical investigation of strain induced magnetization switching in ferromagnetic/ferroelectric hybrid structures — ●MATTHIAS BRASSE^{1,2}, ANDREAS BRANDLMAIER¹, MATTHIAS OPEL¹, GEORG WOLTERS DORF³, RUDOLF GROSS¹, and SEBASTIAN T. B. GOENNENWEIN¹ — ¹Walther-Meißner-Institut, Bayerische Akademie der Wissenschaften, 85748 Garching — ²Lehrstuhl für Physik funktionaler Schichtsysteme, Physik Department, Technische Universität München, James-Frank-Str. 1, 85748 Garching — ³Universität Regensburg, 93040 Regensburg

We report on the investigation of multiferroic hybrid structures, which are promising for the electric field control of the magnetization orientation. The hybrid structures consist of a ferromagnetic thin film evaporated onto a commercially available piezoelectric actuator. Making use of the piezoelectric and the magnetoelastic effect allows to control the magnetization orientation by means of the voltage applied to the piezoelectric actuator.

Spatially resolved magneto-optical Kerr effect measurements were employed to study the magnetization orientation as a function of the applied strain. Using an appropriate measurement sequence, we could

demonstrate the switching of the magnetization between two distinct orientations at constant external magnetic field. We also studied local magnetization switching in the hybrid structures. Our results show, that an electric field control of ferromagnetism is possible via the elastic channel both on macroscopic as well as on microscopic scales.

This work was supported by the DFG via Go 944/3.

MA 10.26 Tue 10:45 Poster A

Giant magnetic anisotropy changes in Sr₂CrReO₆ thin films on BaTiO₃ — ●FRANZ D. CZESCHKA, STEPHAN GEPRÄGS, MATTHIAS OPEL, SEBASTIAN T.B. GOENNENWEIN, and RUDOLF GROSS — Walther-Meißner-Institut, Bayerische Akademie der Wissenschaften, Garching, Germany

The integration of ferromagnetic and ferroelectric materials into hybrid heterostructures leads to systems with improved or even novel functionality. We here discuss the properties of the ferromagnetic double perovskite Sr₂CrReO₆, deposited as a thin film onto ferroelectric BaTiO₃ single crystal substrates via pulsed laser deposition. High resolution x-ray diffraction evidences the high crystalline quality of the epitaxial Sr₂CrReO₆ layers. Temperature dependent electrical transport and SQUID measurements show abrupt changes both in resistivity and magnetization at the temperatures of the BaTiO₃ phase transitions. Furthermore, the coercive field abruptly changes by more than 1.2 T at the BaTiO₃ phase transitions. These observations reveal a giant change of the magnetic anisotropy in the Sr₂CrReO₆ thin film associated with the crystalline phase transitions of the substrate. We attribute these effects to the high sensitivity of the double perovskites to mechanical deformation.

Financial support by the DFG via SPP 1157 and 1285, GO 944/3 and the Excellence Cluster "Nanoinitiative Munich" is gratefully acknowledged.

F. Czeschka et al., Appl. Phys. Lett. **95**, 062508 (2009)

MA 10.27 Tue 10:45 Poster A

Dynamics of driven multiferroic heterostructures — ●ALEXANDER SUKHOV¹, CHENGLONG JIA¹, PAUL HORLEY², and JAMAL BERAKDAR¹ — ¹Institut für Physik, Martin-Luther-Universität Halle-Wittenberg, Heinrich-Damerow-Str. 4, 06120 Halle/Saale, Germany — ²Centro de Fisica das Interacões Fundamentais Instituto Superior Tecnico, Av. Rovisco Pais, 1049-001 Lisboa, Portugal

We study theoretically a ferromagnet (FM) coupled to a ferroelectric (FE) material via a multiferroic coupling. The magnetization dynamics in the ferromagnetic part is described in a standard way via the Landau-Lifshitz-Gilbert equation at finite temperatures with a dynamical driving term arising from the multiferroic coupling. Hence, an electric field that acts on the electric polarization triggers a magnetization dynamics. The ferroelectric dynamics is considered in the framework of the Landau theory of phase transitions and is governed by the Landau-Kholmogorov equation [1] augmented with a dynamical part that stems from the coupling to the ferromagnet, i.e. a magnetic field affects the polarization dynamics. We inspect how the nature of the multiferroic coupling, e.g. [2], is manifested in the time evolution of the order parameters.

[1] D. Ricinchi, C. Harnagea, C. Papusoi, L. Mitoseriu, V. Tura and M. Okuyama, J. Phys.: Condens. Matter **10**, 477 (1998); [2] T. Cai, S. Ju, J. Lee, N. Sai, A. A. Demkov, Q. Niu, Z. Li, J. Shi and E. Wang, Phys. Rev. B **80**, 140415(R) (2009).

MA 10.28 Tue 10:45 Poster A

Thermomechanical properties of mullite up to 1673 K: single crystal vs. ceramics — ●THOMAS FRIEDRICH KRENZEL¹, JÜRGEN SCHREUER¹, and HARTMUT SCHNEIDER² — ¹Ruhr University Bochum, Institute of Geology, Mineralogy and Geophysics, Bochum, Germany — ²University of Cologne, Institute of Crystallography, Köln, Germany

This poster has been moved to MM 26.10.

MA 10.29 Tue 10:45 Poster A

Exchange Bias and Training Effect in Ni/Fe_xMn_{1-x}/Ni Trilayers — ●PAUL STOLL, MIRIAM STAMPE, and WOLFGANG KUCH — Institut für Experimentalphysik, Freie Universität Berlin, Arnimallee 14, 14195 Berlin, Germany

We have investigated ultrathin single-crystalline Ni/Fe_xMn_{1-x}/Ni/Cu(001) trilayers with out-of-plane magnetization. These trilayers show exchange bias due to the interface coupling between the ferromagnetic

(FM) Ni and the antiferromagnetic (AFM) FeMn layers as well as ferromagnetic interlayer coupling between the two FM layers. Hysteresis loops for samples with different FM and AFM layer thickness and FeMn composition have been measured at different temperatures and for opposite cooling fields using polar magneto-optical Kerr effect (MOKE). The hysteresis curves show a two-step magnetization reversal with the coercivities clearly attributed to the switching fields of the two FM layers. In the minor loops unidirectional anisotropy as well as a training effect have been observed.

Financial support by the DFG (KU1115/9-1) is acknowledged.

MA 10.30 Tue 10:45 Poster A

Relative orientation of the magnetic moments in the Fe/MnPd exchange bias system — ●S. BRÜCK^{1,3}, S. MACKÉ¹, X. JI², Q. ZHAN², K. M. KRISHNAN², and E. GOERING¹ — ¹Max-Planck-Institut für Metallforschung, Stuttgart, Germany — ²Department of Materials Science and Engineering, University of Washington, Seattle, USA — ³Physikalisches Institut, Universität Würzburg, Würzburg, Germany

Recent soft X-ray resonant magnetic reflectometry (XRMR) investigations of a Fe/MnPd exchange bias system have revealed a complex magnetic configuration at the ferromagnet (F)/antiferromagnet (AF) interface in the system[1]. The existence of a considerable amount of rotatable uncompensated magnetic moments in the antiferromagnet as well as the confinement of pinned uncompensated moments to the F|AF interface was shown. Precise knowledge of the location and relative orientations of all kinds of magnetic moments at the F|AF interface is a necessary prerequisite for the development of new models for the description of exchange bias. We show how by comparing the signs and magnitudes of the absorptive part of the index of refraction, it is possible to determine the relative coupling directions in the system. It is found that rotatable Mn and the ferromagnetic Fe couple antiparallel. The pinned Mn moments are oriented antiparallel to the neighboring rotatable Mn and parallel with respect to the Fe during the field cooling process.

[1] S. Brück, G. Schütz, E. Goering, X. Ji, and K. M. Krishnan, Phys. Rev. Lett. **101**, 126402-4 (2008).

MA 10.31 Tue 10:45 Poster A

Investigation of exchange bias field of NiMn pinned Co nanoparticles — ●BALATI KUERBANJIANG, BENJAMIN RIEDMÜLLER, and ULRICH HERR — Institut für Mikro- und Nanomaterialien, Universität Ulm, 89081, Ulm, Germany

Co nanoparticles deposited on a sputtered NiMn layer have been studied for the purpose of the exchange bias field. About 30 nm of NiMn layer was deposited on Si substrate by magnetron sputtering, then Co nanoparticles were deposited in situ on the NiMn layer using inert gas condensation technique. Samples were subsequently covered by about 5 nm of Cu in order to prevent oxidation of particles in air. Chemical states and compositions of the samples were examined by XPS inside the UHV system. Ex situ annealing has been carried out to achieve the antiferromagnetic NiMn phase at 350 °C for 10 min, in an applied field of 350 Oe. Annealing was performed under vacuum to avoid degradation of the magnetic properties. The phase transformation of the NiMn was investigated by X-ray diffraction. The size and the coverage of Co nanoparticles has been determined by AFM and SEM. The influence of the magnetic interaction between NiMn AFM layer and the FM Co particles of different sizes and densities was studied using vibrating sample magnetometry (VSM), magneto-optical Kerr effect (MOKE) and magnetic force microscopy (MFM).

MA 10.32 Tue 10:45 Poster A

Long and short term changes of the exchange bias field in MnIr/CoFe bilayers after ion bombardment with 10keV He ions — ●CHRISTOPH SCHMIDT, JÖRN BURBANK, NIKLAS STEIN, TANJA WEIS, DIETER ENGEL, and ARNO EHRESMANN — Department of Physics, University of Kassel, Heinrich-Plett-Str.40, D-34132 Kassel

The stability and time dependence of the exchange bias (EB) field after 10 keV He⁺ ion bombardment (IB) were studied. The long term measurements were done ex-situ in a time window between half an hour and several weeks after IB and the short term measurements in-situ between a few seconds and half an hour after IB. The following changes were observed: (i) the long term changes have a logarithmic behaviour of the EB field to larger values while (ii) the short term investigations show an exponential decrease of the EB field and a relaxation back to its origin direction of the unidirectional anisotropy. The two different behaviours depend on the time scale of the measurements after IB.

MA 10.33 Tue 10:45 Poster A

Remote control of superparamagnetic nanobeads on magnetically patterned thin films — •DANIEL LENGEMANN, TANJA WEIS, ALLA ALBRECHT, JANNICK LANGFAHL-KLABES, DIETER ENGEL, and ARNO EHRESMANN — University of Kassel, Heinrich-Plett-Str. 40, 34132 Kassel, Germany

He-ion bombardment were used to get a periodic magnetic patterning with alternating anisotropy directions in exchange biased MnIr/CoFe thin layers. In remanence superparamagnetic nanobeads were located at the domain walls where the strong stray fields reach their maximum. Within an external inhomogeneous magnetic field it is possible to saturate the sample, i.e. the periodic magnetic patterning and therewith the stray fields vanish and the nanobeads can follow the gradient of the field. This mechanism allows a controlled movement of the nanobeads. First results are shown.

MA 10.34 Tue 10:45 Poster A

Coercivity mechanism in hard magnetic SmCo₅/PrCo₅ bilayers — •FELIX FLEISCHHAUER, VOLKER NEU, and LUDWIG SCHULTZ — IFW Dresden, Institute of Metallic Materials, 01069 Dresden, Germany

The evolution of the coercivity in hard magnetic SmCo₅/PrCo₅ bilayers shows a non-trivial dependence on the relative sublayer thickness and the stacking order.

These dependencies have been studied for bilayers with 40 nm overall thickness. They were epitaxially grown on Cr buffered MgO(110) substrates using pulsed laser deposition technique. Temperature dependent coercivity was measured in the range from 200 K to 400 K along with the magnetic relaxation at room temperature. The results are discussed within the framework of several pinning concepts.

MA 10.35 Tue 10:45 Poster A

Single or multichannel Kondo effect in graphene — •ZHENG-GANG ZHU¹, KAI-HE DING², and JAMAL BERAQDAR¹ — ¹Institut für Physik, Martin-Luther Universität Halle-Wittenberg, Heinrich-Damerow-Straße 4 06120 Halle, Germany — ²Department of Physics and Electronic Science, Changsha University of Science and Technology, Changsha 410076, China

Dynamic screening in a Kondo system may compensate or over compensate for the localized magnetic moment signifying respectively a Fermi or a non-Fermi liquid ground state. The former (latter) case occurs in one (two) channel Kondo effect with a magnetic impurity having spin 1/2. We investigate this issue in graphene starting from the tight-binding Anderson model. Schrieffer-Wolff transformation is performed to derive the Kondo model. To verify our findings, we also conduct direct computations by considering the two-body interaction explicitly. At last, the Kondo temperature is calculated from Anderson model in the large U limit. We find: i) for nearest neighbor hopping, a two-channel Kondo character is present when the impurity is symmetrically coupled to the A and B sublattice; otherwise a single channel Kondo is realized. ii) The exchange interaction coefficient for one channel is vanishing when the spin is symmetrically coupled to the spanned sublattice to this channel in absence of a gate voltage. However it is finite in the presence of a gate voltage. iii) The degeneracy of the two Dirac points leads only to a higher Kondo temperature which is increasing exponentially with increasing gate voltage. We point out the experimental feasibility by varying a gate voltage.

MA 10.36 Tue 10:45 Poster A

Magnetotransport measurements on Heusler compounds — •A. KRUPP¹, F.D. CZESCHKA¹, M. ALTHAMMER¹, S.T.B. GOENNENWEIN¹, R. GROSS¹, I.-M. IMORT², G. REISS², and A. THOMAS² — ¹Walther-Meißner-Institut, Bayerische Akademie der Wissenschaften, Garching, Germany — ²Fakultät für Physik, Universität Bielefeld, Bielefeld, Germany

Magnetic anisotropy (MA) is of fundamental importance in ferromagnets, as it strongly influences their properties. Using magnetotransport measurements, we investigate the MA of the Heusler compound Co₂FeAl. A 20 nm thick Co₂FeAl film on (001)-oriented MgO substrate was patterned into Hall-bar mesa structures with optical lithography and etching. The anisotropic magnetoresistance (AMR) is then measured with the external magnetic field applied in the film plane. The measured longitudinal and transverse resistance show a clear field dependence with distinct steps at small external magnetic fields ($\mu_0 H$), indicating abrupt switching of the magnetization orientation. To quantify the MA, we record the angle dependent magne-

toresistance (ADMR), i.e. the MR as a function of H -orientation for different magnetic field magnitudes $|H|$. From the ADMR data taken at high $|H|$, AMR coefficients are obtained. The MA is then extracted from ADMR at lower $|H|$. We obtain a cubic MA field of around $\mu_0 H_{\text{cub}}=5$ mT and an uniaxial MA field of around $\mu_0 H_{\text{uni}}=1$ mT. We also discuss the evolution of MA with temperature and compare our results to literature.

MA 10.37 Tue 10:45 Poster A

Anomalous Hall Effect in Heusler Compounds — •I.-M. IMORT¹, G. REISS¹, A. THOMAS¹, A. KRUPP², F.D. CZESCHKA², M. ALTHAMMER², R. GROSS², and S.T.B. GOENNENWEIN² — ¹Fakultät für Physik, Universität Bielefeld, Bielefeld, Germany — ²Walther-Meißner-Institut, Bayerische Akademie der Wissenschaften, Garching, Germany

The anomalous Hall Effect (AHE) is a fundamental but still controversially discussed phenomenon in ferromagnets. Furthermore, it is a volatile characterization tool for magnetic materials. We here report on our magnetotransport experiments and the AHE in the Heusler compound Co₂FeAl. Using rf-magnetron sputtering, 20 nm thick Co₂FeAl thin films were grown on single-crystal MgO(001) substrates. Before patterning into 80 μm wide Hall bars, some of the samples were annealed at different temperatures. The Hall resistivity ρ_{xy} and the magnetoresistivity ρ_{xx} were measured simultaneously over a temperature range of 3 to 300 K and a magnetic field range of $|H|$ T. For low magnetic fields $\mu_0 H$, ρ_{xx} exhibits typical anisotropic magnetoresistance features, with resistance jumps and a non-linear dependence on H . This behaviour abruptly changes at higher fields: for $\mu_0 H \geq 1.6$ T, ρ_{xx} scales strictly linearly with H . In contrast, the Hall resistivity always is proportional to $|H|$, but the slope of ρ_{xy} abruptly changes sign at $\mu_0 H \approx 1.6$ T. We will discuss the impact of temperature, surface roughness and annealing temperature on the magnetotransport properties and compare our results to the literature.

MA 10.38 Tue 10:45 Poster A

Annealing time and temperature dependence of structural, magnetic and transport properties of Co₂MnSi-based MTJs — •HENDRIK WULFMEIER, MARKUS MEINERT, DANIEL EBKE, JAN SCHMALHORST, and GÜNTER REISS — Bielefeld University, Thin Films and Physics of Nanostructures, Department of Physics, Universitätsstr. 25, D-33615 Bielefeld, Germany

A high tunnel magnetoresistance effect (TMR) in magnetic tunnel junctions (MTJs) is the key for developing new spintronic devices like MRAM or magnetic sensors.

Optimization of MTJ-stacks where at least one electrode is built of a Heusler-alloy has been topic of many studies in recent time.

In order to enhance the level of crystallinity post-annealing is very successful. In general this effect is limited by interdiffusion processes at the interfaces of the individual layers. Crystallization and interdiffusion are both time- and temperature-dependent processes.

In our study we investigated not only the effect of different annealing temperatures but also the influence of different annealing times on the crystal structure and on the electronic properties. We prepared half (Co₂MnSi | MgO) and full (Co₂MnSi | MgO | CoFe | MnIr) MTJs on MgO(001)-substrates by sputter deposition and used x-ray diffractometry, MOKE and standard transport measurements for characterization.

The comparison of the experimental results (structural, magnetic and transport properties) will be discussed.

MA 10.39 Tue 10:45 Poster A

Magnetic transport measurements of epitaxial SmCo₅ in pulsed magnetic fields — •EVELYN STILP, ALEXANDER KAUFFMANN, MARIETTA SEIFERT, JENS FREUDENBERGER, VOLKER NEU, NADEJDA KOZLOVA, and LUDWIG SCHULTZ — IFW Dresden, Institute for Metallic Materials, Helmholtzstr. 20, 01069 Dresden, Germany

SmCo₅ is a hard ferromagnetic material with a high Curie temperature around 800°C and a high coercivity of 3T. With the help of a Quantum Design PPMS vibrating sample magnetometer magnetic properties were already measured. Hence an anisotropy field of 28T was calculated [1]. The epitaxial SmCo₅ thin films were prepared by pulsed laser deposition on Cr buffered MgO(110) [2]. Hall measurements of SmCo₅ thin films will be presented.

[1] A. Singh *et al.*, Phys. Rev. B 77, 104443 (2008)[2] A. Singh and V. Neu *et al.*, J. Appl. Phys. 99, 08E917 (2006)

MA 10.40 Tue 10:45 Poster A

Epitaxial NdCo₅/SmCo₅ bilayers — •MARIETTA SEIFERT, LUD-

WIG SCHULTZ, and VOLKER NEU — IFW Dresden, Helmholtzstr. 20, 01069 Dresden, Germany

RECO₅ magnets are of interest due to their strong magnetocrystalline anisotropies, which in some cases change with temperature. This work presents epitaxial NdCo₅/SmCo₅ bilayers, in which NdCo₅ undergoes a spin reorientation transition from easy axis along the *c*-axis above 310 K to easy plane below 255 K while SmCo₅ keeps the uniaxial anisotropy in the whole temperature range. The films were prepared on Cr buffered MgO(110) substrates resulting in a growth of the RECO₅ with a single orientation of the *c*-axis parallel to the film plane. In a first step, the magnetic behavior of single NdCo₅ thin films have been investigated and it was found that they possess intrinsic magnetic properties and especially a spin reorientation transition in good agreement with single crystal data. To analyze the magnetic coupling of the bilayer system, a series with a fixed thickness of the SmCo₅ layer and a varying thickness of the NdCo₅ have been prepared. Phase formation and texture were controlled with XRD and texture measurements. The magnetic properties in a temperature range between 20 and 400 K have been measured with Vibrating Sample Magnetometry.

MA 10.41 Tue 10:45 Poster A
Remanence enhancement and energy density in epitaxial exchange-coupled SmCo₅/Fe-Multilayers — ●SIMON SAWATZKI, FELIX FLEISCHHAUER, MARIETTA SEIFERT, LUDWIG SCHULTZ, and VOLKER NEU — IFW Dresden, Institute for Metallic Materials, P.O. Box 270116, D-01071 Dresden, Germany

Exchange-coupled SmCo₅/Fe-multilayers have been epitaxially grown by pulsed laser deposition on Cr covered MgO(110) substrates, such that one single in-plane easy axis of the highly anisotropic SmCo₅ phase is realized through the whole layer stack. The phase formation and texture was confirmed by Bragg-Brentano X-ray diffraction and pole figure measurements. The magnetic properties were characterized by vibrating sample magnetometry. In order to maximize the energy density (BH)_{max}, as a key property for permanent magnet application, two series of samples were investigated. First, trilayers of SmCo₅/Fe/SmCo₅ with fixed SmCo₅ layer thickness (25 nm) and varying soft magnetic Fe film thickness have been prepared to analyze the impact of the Fe-volume fraction on remanence enhancement and coupling. In the second series SmCo₅/Fe alternating multilayer with constant Fe-volume fraction but reduced single layer thickness were examined.

MA 10.42 Tue 10:45 Poster A
Epitaxial NbFe₂ thin films prepared by PLD — ●ANDREAS REISNER, SILVIA HAINDL, BERNHARD HOLZAPFEL, and LUDWIG SCHULTZ — IFW Dresden, Institute of Metallic Materials, 01069 Dresden, Germany

The hexagonal Laves phase NbFe₂ shows an interesting itinerant magnetic behaviour whose ferromagnetic transition at low temperatures is strongly dependent on the stoichiometry.

We report on successful preparation of epitaxial thin films grown on single crystalline Al₂O₃ (001) substrates by an UHV pulsed laser deposition process. Structural investigation show a twofold epitaxial relation of Al₂O₃(001)[100]||NbFe₂(001)[100] and Al₂O₃(001)[100]||NbFe₂(001)[210]. Magnetic and transport properties of films with various compositions near the stoichiometric point have been investigated.

MA 10.43 Tue 10:45 Poster A
In-Situ STM, LEED and MOKE Measurements of Ultrathin Epitaxially Flat Grown Fe Films on the GaAs(110) Surface — ●TIM IFFLÄNDER, MARTIN WENDEROTH, THOMAS DRUGA, and RAINER G. ULBRICH — IV. Physikalisches Institut, Georg-August-Universität Göttingen

Fe films of up to 8 ML thickness were deposited on cleaved n-, p- and i-GaAs(110) in a two-step process combining low-temperature deposition at 130 K with a subsequent annealing to room temperature. Low-energy electron diffraction and scanning tunnelling microscopy suggest an abrupt interface without any considerable amount of compound formation and a flat continuous morphology with height variations in the monolayer range.

In-situ longitudinal magneto-optical Kerr effect measurements at RT were conducted for different in-plane orientations of the applied magnetic field with respect to the sample. In contrast to RT grown Fe films of 2-3 ML thickness, the easy and hard axes are interchanged, now parallel to the [001] and [110] directions, respectively. The hysteresis loop

of films thicker than or equal to 5 ML is equivalent to magnetization curves observed in the case of RT grown films.

This work was supported by the SFB 602 TP A7.

MA 10.44 Tue 10:45 Poster A
Magnetic and structural investigations of iron based nanostructures and thin CrSb layers on GaAs(110) — ●CARSTEN GODDE, SANI NOOR, ATENA RASTGOO LAHROOD, GREGOR NOWAK, HARTMUT ZABEL, and ULRICH KÖHLER — Institut für Experimentalphysik IV, Ruhr-Universität Bochum, Germany

In this contribution we present structural and magnetic measurements of the two different systems, Fe and CrSb layers on the GaAs(110) surfaces.

We investigate the growth of Fe on the GaAs(110) surface at different coverages and annealing temperatures by STM and MOKE and show that the structure remains ferromagnetic up to 500°C in combination with lateral structuring on the nanometer scale. These nanostructures consist exclusively of roof-shaped 3D-islands elongated along the [1 $\bar{1}$ 0]-direction of the GaAs(110) substrate. An intermixing of the Fe film and the substrate material induced by the annealing step leads to a ternary alloy Fe₃Ga_{2-x}As_x which is confirmed by X-ray diffraction measurements. Despite of this alloying it should be noted that the magnetic measurements of the nanostructures still show ferromagnetic characteristics.

Thin CrSb layers grow in the zinc blende structure and contrary to the Fe system they keep their ferromagnetic properties and structural stability up to very high annealing temperatures which is interesting for enabling better crystalline quality. In this context the CrSb layers were characterised by STM, LEED and SQUID magnetometry at different coverages and annealing temperatures.

MA 10.45 Tue 10:45 Poster A
Structural and magnetic investigations of Fe and Fe₃Si as CEO-grown spin aligning layers on spin LEDs — ●SANI NOOR¹, CARSTEN GODDE¹, HASMIK HARUTYUNYAN¹, ARNE LUDWIG², MINGYUAN LI³, GREGOR NOWAK¹, DIRK REUTER², MARTIN HOFMANN³, HARTMUT ZABEL¹, ANDREAS WIECK², and ULRICH KÖHLER¹ — ¹Experimentalphysik IV, Ruhr-Universität Bochum — ²Angewandte Festkörperphysik, Ruhr-Universität Bochum — ³Photonik und Terahertztechnologie, Ruhr-Universität Bochum

We focus on the the structural and magnetic properties of Fe and Fe/MgO as spin injection layers on the GaAs(110) cleaved edge of spin LEDs. Within the scope of our work, we have developed an in situ process to cleave the sample within a μm range of the designated edge and deposit the layers. We show a MOKE study of the magnetization behaviour in the case of Fe which forms a Schottky barrier on n-GaAs and Fe with an MgO interlayer as a tunnelling barrier as a function of the layer thickness. STM images of Fe grown on μm -wide terraces of the cleaved GaAs(110) surface are also presented. Finally, we discuss the results of electroluminescence measurements to determine the efficiency of spin injection across the cleaved edge.

We furthermore present an STM growth study of Fe₃Si/GaAs which as a Heusler alloy is also a possible candidate as a spin aligner. In contrast to Fe/GaAs we find layer-by-layer growth even above RT. Epitaxial and stoichiometrical quality has been confirmed by XRD and LEED. Our angular dependent in situ MOKE measurements show that the Fe₃Si/GaAs(001) system exhibits only a weak magnetic anisotropy.

MA 10.46 Tue 10:45 Poster A
Threshold photoemission magnetic circular dichroism at the spin reorientation transition of ultrathin epitaxial Pt/Co/Pt(111)/W(110) films — ●KERSTIN HILD, JAKOB EMMEL, GERD SCHÖNHENSE, and HANS-JOACHIM ELMERS — Institut für Physik, Johannes Gutenberg-Universität Mainz, Germany

We report on the thickness dependence of threshold photoemission magnetic circular dichroism (TPMCD [1]) in one- and two-photon photoemission (1PPE and 2PPE) for a Pt-capped ultrathin Co wedge grown on Pt(111)/W(110) using femtosecond laser light. TPMCD measurements result in asymmetries continuously increasing with the sample thickness. This indicates that the TPMCD asymmetry is dominantly influenced by the Co bulk properties. At 5 monolayers (ML) asymmetry values of 0.07 % for 1PPE and 0.11 % for 2PPE are derived. The spin reorientation transition is detected at a Co thickness of 5.5 ML. For the perpendicularly saturated sample the TPMCD does not depend on the orientation of the easy axis. The comparison of the 2PPE TPMCD asymmetries with measured Kerr ellipticities in the framework of the Jones formalism reveals considerable differences

between both quantities.

Funded by DFG (EL 172/15-1), the Carl-Zeiss-Stiftung and the Graduate School of Excellence MAINZ (Kerstin Hild). [1] K. Hild et al., J. Phys.: Condens. Matter 20, 235218 (2008).

MA 10.47 Tue 10:45 Poster A

Magnetization reversal and reorientation in DyCo₅ systems — ●RADU ABRUDAN¹, ILIE RADU², DETLEF SCHMITZ³, HARTMUT ZABEL¹, and FLORIN RADU³ — ¹Experimentalphysik IV, Ruhr-Universität Bochum, 44780 Bochum, Germany — ²Institute for Molecules and Materials, Radboud University Nijmegen, 6525 ED Nijmegen, The Netherlands — ³Helmholtz-Zentrum Berlin für Materialien und Energie GmbH, 12489 Berlin, Germany

DyCo₅ is a ferrimagnet which develops a compensation point (CP) at low temperatures where the magnetic structure switches 180 degrees, a spin reorientation (SR) point at a temperature higher than room temperature, where the magnetisation axis of Dy and Co drops in plane, parallel to the substrate.

We present a systematic study of sputter deposited DyCo₅ thin films using XMCD technique in a transmission geometry. The spin and orbital magnetic moments of Co and Dy exhibit a monotonous temperature dependence. The ferrimagnetic alignment between the Dy and Co moments is preserved across both phase transitions, occurring at the spin reorientation ($T_{SR} \sim 350$ K) and at the compensation ($T_{CP} \sim 120$ K) temperatures, respectively. Notably, the magnetic crystalline anisotropy changes orientation from in-plane at high temperatures to out-of-plane below T_{SR} . At T_{CP} the coercive field is strongly enhanced, diverging in size due to the reduced averaged magnetization specific to ferrimagnetic systems. Moreover, the orientation of the magnetic moments of Dy and Co reverses sign when crossing the T_{CP} .

MA 10.48 Tue 10:45 Poster A

Transition from shape anisotropy to magnetocrystalline anisotropy in ultrathin FePt films — ●KARIN LEISTNER, JULIANE WUNDERWALD, SEBASTIAN FÄHLER, and LUDWIG SCHULTZ — IFW Dresden, Dresden, Germany

FePt films have recently attracted great interest as possible media for perpendicular magnetic recording, but also for fundamental studies of magnetism in reduced dimensions. As FePt it is very corrosion resistant it is ideal for ultrathin films, however, L10 ordering and thus high magnetocrystalline anisotropy are harder to achieve at small particle size. In the present study, 2 nm thick FePt films have been deposited by pulsed laser deposition on MgO(001) with a Cr/Pt buffer. The magnetic properties have been obtained by Hall measurements and measurements of the Kerr rotation. Without post annealing, the out-of-plane (op) hysteresis is controlled by shape anisotropy with an anisotropy field of 1.4 T. The easy axis lies in-plane and in the op hysteresis curve rotation of magnetization is observed. This is as expected for smooth ultrathin disordered FePt films. When post annealing is applied, a continuous decrease of the effective in-plane anisotropy field is observed with increased annealing time. After a post annealing time of 15 min, the easy axis lies op and the op hysteresis shows switching of magnetization and a larger coercivity. The reason is that ordering in the (001)-textured films leads to an increased magnetocrystalline anisotropy in the op direction that competes with shape anisotropy. Thus, in these ultrathin FePt films anisotropy can be continuously adjusted from pure shape anisotropy to magnetocrystalline anisotropy.

MA 10.49 Tue 10:45 Poster A

Design and preparation of substrates with perpendicular magnetic anisotropy for molecular magnets — ●JONATHAN FETTING¹, JAN-PHILIPP GROTE¹, MICHAEL STOCKER², MICHAEL ENZELBERGER², VERONIKA HÖKE³, CARL-GEORG FRHR. V. RICHTHOFEN³, PAUL MÜLLER², THORSTEN GLASER³, and GÜNTER REISS¹ — ¹Bielefeld University, Department of Thin Films and Physics of Nanostructures, Universitätsstr. 25, 33615 Bielefeld — ²University Erlangen-Nürnberg Physikalisches Institut III, Erwin-Rommel-Str. 1, 91058 Erlangen — ³Bielefeld University, Department of Inorganic Chemistry, Universitätsstr. 25, 33615 Bielefeld

In spintronics thin films with out of plane magnetization are highly desirable for, e.g., electrodes in tunnelling cells or substrates for molecular magnets. The goal of our work is to be able to define desired film properties and to tailor the thin films correspondingly. For our approach we have chosen [CoPd]_x as hard magnetic and [CoAu]_x as soft magnetic multilayers. Mixing those multilayer systems gives the possibility to design the material properties. The multilayer systems

have been prepared using sputter deposition techniques and the resulting thin films have been investigated with AGM, STM and MFM. The measurements give an insight into the structural and magnetic properties of the tailored samples and improve the ability to property design.

MA 10.50 Tue 10:45 Poster A

Imaging of magnetic coupling in trilayered microstructures — ●JULIA KURDE¹, JORGE MIGUEL¹, DANIELA BAYER², JAIME SÁNCHEZ-BARRIGA³, LOGANE TATI BISMATHS³, MARTIN AESCHLIMANN², HERMANN A. DÜRR³, and WOLFGANG KUCH¹ — ¹Freie Universität Berlin — ²Technische Universität Kaiserslautern — ³Helmholtz-Zentrum Berlin für Materialien und Energie

Magnetic properties of microstructures consisting of either an FeNi single layer or an FeNi/Cu/Co trilayered system were investigated by means of photoelectron emission microscopy. We performed stroboscopic pump-probe experiments to determine the precession frequencies and the effective field of the FeNi layer. From the comparison of these measurements to micromagnetic simulations, the coupling field in the trilayered systems could be extracted. This information can then be used to explain the observed domain wall (DW) configurations in the FeNi layer. The parallel coupling of the two magnetic layers via the non-magnetic spacer layer is dominated by Néel coupling. However, the strong stray field of the DWs in the Co layer forces the magnetization to align antiparallel in the two layers, and so to turn with opposite sense of rotation from domain to domain. In 180° walls, a left turn is symmetric to a right turn, but in 90° walls of the Co layer, this will lead to a 270° turn of the magnetization in the FeNi layer. Although this case is highly unfavorable with respect to the exchange interaction within the FeNi layer, it still occurs if the Cu spacer layer reduces sufficiently the Néel coupling to the Co layer.

This work has been supported by the BMBF 05 KS7 KE2

MA 10.51 Tue 10:45 Poster A

Magnetostrictive Strain Sensors Based on FeGa Thin Films — ●AHMED FAZIR THAJUDIN, DIRK MEYERS, and ECKHARD QUANDT — Chair for Inorganic Functional Materials, Institute for Materials Science, Faculty of Engineering, University of Kiel, Kaiserstr. 2, 24143 Kiel, Germany

Tunneling magnetoresistance junctions generally possess a symmetrical characteristic which reflects the switching fields of the soft and hard layers, respectively. This characteristic can be changed by a stress field if the soft magnetic layer is replaced by a suitable magnetostrictive layer. Application of mechanical stress results in a stress induced rotation of the magnetostrictive layer with respect to the reference layer accompanied by a resistance change due to the magnetoresistance effect. Highly sensitive strain sensors with CoFeB electrodes based on this concept were developed recently [1]. Further increase of sensitivity is expected by the introduction of highly magnetostrictive FeGa layers. The magnetic and magnetostrictive properties of magnetron sputtered FeGa thin films are discussed. Moreover, tunneling magnetoresistance stacks with FeGa sensing layers were prepared, patterned by optical lithography and investigated with respect to microstructure, effect amplitude and magnetic switching behavior.

[1] D. Meyners, T. von Hofe, M. Vieth, M. Rührig, S. Schmitt, and E. Quandt, J. Appl. Phys. 105, 07C914, 2009

MA 10.52 Tue 10:45 Poster A

Influence of strain on magnetic and electrical properties of La_{0.82}Sr_{0.18}CoO₃ films — ●ORKIDIA BILANI-ZENELI, DIANA RATA, ANDREAS HERKLOTZ, LUDWIG SCHULTZ, and KATHRIN DÖRR — IFW Dresden, Institute for Metallic Materials, Helmholtzstrasse 20, 01069 Dresden, Germany

Cobaltite perovskites La(1-x)Sr(x)CoO₃ have received attention mainly due to the thermally driven spin state transitions of the Co ions. For different doping, these transitions have been shown to be sensitive towards pressure in bulk and epitaxial strain in thin films. La(1-x)Sr(x)CoO₃ with x=0.18 is of particular interest because it is located near the boundary of the Metal-Insulator transition. We have grown epitaxial La_{0.82}Sr_{0.18}CoO₃ (LSCO) thin films by pulsed laser deposition on different substrates (PMN-PT, LaAlO₃, SrTiO₃, LSAT) providing reversible and static strain. In this work the influence of biaxial strain on the magnetic and electrical transport properties of LSCO films will be presented. Thin films reveal significant differences in magnetic behaviour with respect to bulk, e.g. the coercive fields are strongly enhanced. On the other hand tensile strain strongly suppresses the electrical conduction stabilizing thus an insulator state.

MA 10.53 Tue 10:45 Poster A

Specular and off-specular scattering of neutrons from Si-Fe multilayers — ●ANKE TEICHERT, THOMAS KRIST, JAN E. HOFFMANN, AMITESH PAUL, and ROLAND STEITZ — Helmholtz Zentrum Berlin, Hahn-Meitner-Platz 1, 14109 Berlin, Germany

Multilayers (ML) are used as neutron optical devices. These applications require high quality MLs with low interface layer thickness, roughness and high remanence as characterized by a high reflectivity and high polarization efficiency. Here, we want to produce high quality stress-free Si-Fe MLs on Si and glass substrate. All samples (10(10nm Si+10nm Fe)+10nm Si) were produced in a triode sputter machine at $p=0.065\text{Pa}$ and Bias voltages from 10 to 65V. Stress and reflectivity measurements were performed at a profilometer and X-ray reflectometer (XRR). Using polarized neutron reflectometry (PNR) and a positive sensitive detector (PSD) at the reflectometer V6 we measured simultaneously specular and off-specular scattering of neutrons. We find a raise in voltage leads to linear decrease of tensile stress with a slope of 5.5MPa/V . At about 60V the samples are nearly stress-free. The grain size decreased with higher Bias voltage. The off-specular data show large diffuse scattering from all samples at low applied magnetic fields (200G, 20G) as well as for samples with high compressive stress at 1030G. It appears as streaks perpendicular to specular reflectivity at Bragg peak positions. They can be interpreted as originating from vertically correlated in-plane magnetic domains. Associated longitudinal fluctuations produce additional diffuse streaks along Bragg peak positions which are independent of the stress within the samples.

MA 10.54 Tue 10:45 Poster A

Soft x-ray magnetic dichroism of undoped, hole-doped and electron-doped LaCoO_3 : Anisotropies and valence-dependent magnetism — ●MICHAEL MERZ¹, CHRISTIAN PINTA^{1,2}, ANDREI SAMARTSEV^{1,2}, MARKUS WISSINGER^{1,2}, HILBERT VON LÖHNEYSEN^{1,2}, ANDREA ASSMANN^{1,2}, STEPHAN UEBE^{1,2}, DIRK FUCHS¹, PETER NAGEL¹, and STEFAN SCHUPPLER¹ — ¹Karlsruhe Institute of Technology, Institut für Festkörperphysik, Germany — ²Karlsruhe Institute of Technology, Physikalisches Institut, Germany

Epitaxial thin films of undoped LaCoO_3 , of electron-doped $(\text{La,Ce})\text{CoO}_3$, and of hole-doped $(\text{La,Sr})\text{CoO}_3$ exhibit ferromagnetic order with optimum transition temperatures of 80 K, 30 K, and 240 K, respectively. The spin-state structure for these compounds was studied by soft x-ray absorption and magnetic circular dichroism at the Co $L_{2,3}$ and O K edges. It turns out that for epitaxial LaCoO_3 , strain imposed by the substrate preserves a higher spin state of the Co^{3+} ions at low temperature and prevents a non-magnetic ground state. For $(\text{La,Ce})\text{CoO}_3$, the Co^{3+} ions are predominantly in a low-spin ($S = 0$) state and thus magnetically inactive, and the ferromagnetism is determined by the Co^{2+} species. For $(\text{La,Sr})\text{CoO}_3$, on the other hand, the magnetism originates from higher spin states of Co^{3+} ($S = 2$) and Co^{4+} ($S = 3/2$) ions. The data show that ferromagnetism has a different origin in LaCoO_3 (superexchange), $(\text{La,Ce})\text{CoO}_3$ (spin blockade), and $(\text{La,Sr})\text{CoO}_3$ (double exchange). Moreover, a strong magnetic anisotropy is observed for all systems, with the spin and the orbital moments essentially lying within the substrate plane.

MA 10.55 Tue 10:45 Poster A

Soft x-ray magnetic dichroism of $(\text{Ca,Sr})\text{RuO}_3$: Evidence for strain-dependent magnetism — ●ANDREA ASSMANN^{1,2}, STEPHAN UEBE^{1,2}, MICHAEL MERZ¹, MARKUS WISSINGER^{1,2}, HILBERT VON LÖHNEYSEN^{1,2}, DIRK FUCHS¹, PETER NAGEL¹, and STEFAN SCHUPPLER¹ — ¹Karlsruhe Institute of Technology, Institut für Festkörperphysik, Germany — ²Karlsruhe Institute of Technology, Physikalisches Institut, Germany

The $4d$ transition metal oxide $\text{Ca}_{1-x}\text{Sr}_x\text{RuO}_3$ exhibits ferromagnetic order in the doping range $0.4 \lesssim x \lesssim 1$ while it is a paramagnetic metal for $x \lesssim 0.4$. Since $\text{Ca}_{1-x}\text{Sr}_x\text{RuO}_3$ remains essentially isostructural and has a similar electronic configuration throughout the doping series, the differences in the magnetic properties might be caused by chemical pressure or magnetic dilution. To verify a possible dependence of the magnetic moments on pressure, $(\text{Ca,Sr})\text{RuO}_3$ films were deposited on different substrates (LSAT, STO, DyScO_3 =DSO), with the lattice mismatch imposing a specific strain on the epitaxial films that increases when going from LSAT to STO and DSO. The magnetic and electronic structure of the strained samples was studied by soft x-ray absorption and magnetic circular dichroism at the Ru $M_{2,3}$ and O K edges. It turns out that at 20 K, the magnetic moments strongly de-

pend on the strain: while the spin moment of samples on LSAT almost vanishes, a distinct moment is found for $(\text{Ca,Sr})\text{RuO}_3$ films deposited on STO and DSO. Furthermore, a significant magnetic anisotropy is observed, with the spin moments mainly oriented perpendicular to the substrate plane. Implications will be discussed.

MA 10.56 Tue 10:45 Poster A

Vector MOKE analysis on ultrathin ferromagnetic films — ●TIMO KUSCHEL¹, HAUKE BARDENHAGEN¹, ROBIN SCHUBERT¹, HENRIK WILKENS¹, DANIEL BRUNS¹, MARTIN SUENDORF¹, BERND ZIMMERMANN¹, FLORIAN BERTRAM², and JOACHIM WOLLSCHLÄGER¹ — ¹Fachbereich Physik, Universität Osnabrück, Barbarastr. 7, 49069 Osnabrück, Germany — ²HASYLAB at DESY, Notkestr. 85, 22607 Hamburg, Germany

In order to study the magnetic reversal and the magnetic anisotropy of ultrathin ferromagnetic films, Fe layers of different thicknesses are assembled on $\text{MgO}(001)$ substrates by Molecular Beam Epitaxy (MBE) under UHV conditions. The films are capped by amorphous silicon to avoid oxidation after leaving the UHV chamber. The structural characterization including X-Ray Reflectivity (XRR) and X-Ray Diffraction (XRD) measurements are performed at HASYLAB (DESY, Hamburg).

The vector MOKE analysis is based on measurements using parallel and perpendicular polarized light as well as external magnetic fields parallel and perpendicular to the incident plane of light to obtain the components of the magnetization vector. A self-programmed tool is used for analyzing the magnetization curves and calculating the magnetization vector for the reversal process of different sample directions.

The results reveal a 180° reversal with a domain splitting involved for the external magnetic field parallel to one of the magnetic easy axis of the sample. The data for the magnetic hard axis show a rotation of the magnetization vector into the magnetic easy axis followed by a 90° reversal and subsequent rotation into the magnetic hard axis back.

MA 10.57 Tue 10:45 Poster A

Quadrupol-Magnetometer für breitbandige Magneto-Optische-Kerr-Spektroskopie — ●MARC TESCH¹, MARKUS GILBERT¹, HANS-CHRISTOPH MERTINS¹, ROMAN ADAM², HERBERT FEILBACH² und CLAUS MICHAEL SCHNEIDER² — ¹FH Münster, Stegerwaldstr. 39, 48565 Steinfurt — ²FZ Jülich, IFF-9, 52425 Jülich

Üblicherweise nutzen Polarimetrieexperimente Laserlicht mit wenigen festen Wellenlängen. Die vorgestellte Polarimetrie-Anlage arbeitet mit einer Entladungsbogenlampe im Spektralbereich von 230nm - 1000nm. Sie ermöglicht Messungen des Faraday- und des Kerr-Effekts wobei ein neuartiges mit FeNdB Permanentmagneten arbeitendes Quadrupol-Magnetometer homogene Magnetfelder von bis zu 570mT in longitudinaler oder transversaler Geometrie erzeugt. Eine Wasserkühlung des inzwischen zum Patent angemeldeten Gerätes ist nicht erforderlich, was einen leichteren Einsatz im UHV ermöglicht. Die Funktionalität der Anlage wird anhand von Reflexions- und Polarisationsmessungen an dünnen Co Einfach- und Mehrschichtsystemen demonstriert und eine Verstärkung des Kerr-Effektes durch Interferenzeffekte diskutiert.

MA 10.58 Tue 10:45 Poster A

Magnetically Induced Optical Nonlinearity in the Centrosymmetric Ferromagnetic Semiconductor EuO — ●MASAKAZU MATSUBARA¹, ANDREAS SCHMEHL², JOCHEN MANNHART², DARRELL SCHLOM³, and MANFRED FIEBIG¹ — ¹HISKP, Universität Bonn, Germany — ²Institut für Physik, Universität Augsburg, Germany — ³Department of Materials Science and Engineering, Pennsylvania State University, USA

EuO is a magnetic semiconductor, which undergoes a ferromagnetic transition at the Curie temperature (T_C) of 69 K. This material exhibits some extreme properties such as a huge colossal magnetoresistance (CMR) effect, the largest magneto-optical effect for any material, and nearly 100% spin polarization of the charge carriers in the ferromagnetic state. These outstanding properties make EuO a very attractive candidate for the basic and applied science of spintronics.

Here we report about the linear and nonlinear optical properties in epitaxial EuO , into which oxygen vacancies are introduced, grown on a YAlO_3 substrate. Even though EuO has a centrosymmetric crystal structure, second-harmonic generation (SHG) was observed below T_C at the two-photon transition energies from the $4f$ to the $5d$ states of Eu^{2+} . The results of the temperature and magnetic field dependent measurements suggest a close correlation between SHG and magnetization. The symmetry analysis provides access to the microscopic origin of this magnetically induced SHG signal.

This work was supported by the Alexander von Humboldt Foundation.

MA 10.59 Tue 10:45 Poster A

Interaction of surface acoustic waves with magnetization dynamics — ●RUPERT HUBER¹, MATHIAS WEILER², SEBASTIAN T.B. GOENNENWEIN², SEBASTIAN NEUSSER¹, and DIRK GRUNDLER¹ — ¹Lehrstuhl für Physik funktionaler Schichtsysteme, Technische Universität München, Physik Department, James-Franck-Str. 1, 85747 Garching b. München, Germany — ²Walther-Meissner-Institut, Bayerische Akademie der Wissenschaften, Walther-Meissner-Strasse 8, 85748 Garching b. München, Germany

The authors investigate the transmission of surface acoustic waves (SAWs) in the GHz regime through thin ferromagnetic films (FM) deposited on a LiNbO₃ substrate. We use e.g. Co and FeCoV. When applying an in-plane magnetic field \vec{H} under different orientations we find characteristic angular dependencies of the SAW's amplitude and phase on \vec{H} . We discuss our observation in terms of the magnetic field dependent change of elastic properties of the FM/LiNbO₃ hybrid systems. The dependencies are investigated in detail by comparing FeCoV and Co. FeCoV is magnetically isotropic, whereas Co shows a pronounced magnetic anisotropy. We find a significant difference for the SAW transmission characteristics. The work has been supported by the German Excellence Cluster "Nanosystems Initiative Munich".

MA 10.60 Tue 10:45 Poster A

Phenomenology of the magnetic shape memory effect in modulated and non-modulated Ni-Mn-Ga and FePd alloys — ●ARISTIDE T. ONISAN and ULRICH K. RÖSSLER — IFW Dresden

Large magnetic shape memory effects in ferromagnetic martensites are observed only in modulated phases, but recently such effects are also demonstrated in the non-modulated (NM) phase of Ni-Mn-Ga with tetragonal crystal structure and $c/a > 1$. The modulated structures have been identified with adaptive, ultra-finely twinned martensite structures of the same tetragonal structure [1]. We develop a phenomenological theory of magnetic martensites based on geometric continuum theory of martensites, linear elasticity, and micromagnetism [2]. A cubic to tetragonal martensitic transition underlies the twinned microstructures, and magnetic anisotropy is modelled by easy-axis or easy-plane uniaxial anisotropy with four-fold in-plane anisotropy. Equilibrium phase diagrams for the distribution of crystallographic variants and magnetic domains are calculated in dependence on external magnetic fields and stresses. Applications are presented for the easy-axis system with materials parameters for 5M-type Ni₂MnGa, and for FePd and NM Ni₂MnGa as easy-plane systems. Modulated phases like 5M are constructed by second-order twinning within the concept of adaptive martensites [1]. Their magnetic properties depend on the relation between magnetic exchange length and modulation period.

[1] S. Kaufmann et al., arXiv:0906.5365. [2] A.N. Bogdanov, A. DeSimone, S. Müller, U.K. Rößler, J. Magn. Mater. 261 (2003) 204-209. Supported by DFG, SPP 1239.

MA 10.61 Tue 10:45 Poster A

Surface structure and electronic properties of epitaxial off-stoichiometric Ni-Mn-Ga films — ●ALEKSEJ LAPTEV¹, PHILIPP LEICHT¹, MIKHAIL FONIN¹, YUANSU LUO², KONRAD SAMWER², YURIY DEDKOV³, and MARTIN WESER³ — ¹Fachbereich Physik, Universität Konstanz, 78457 Konstanz — ²I. Physikalisches Institut, Georg-August-Universität Göttingen, 37077 Göttingen — ³Fritz-Haber-Institut der Max-Planck-Gesellschaft, 14195 Berlin

Ni₂MnGa alloys have attracted considerable interest due to the large magnetic field-induced strain and their possible applications as microscale actuators or sensors. Upon cooling from the austenite phase a transformation to the martensite phase occurs for these materials. Here we report on the investigation of epitaxial off-stoichiometric Ni-Mn-Ga films grown on MgO substrates by dc-magnetron sputtering. To achieve appropriate surface quality the samples were treated under ultra high vacuum conditions by repeated cycles of sputtering and annealing. The crystal structure changes at the Ni-Mn-Ga (100) surface during the reversible phase transition were followed by LEED. A splitting of the main reflexes due to a longer range ordering of the surface was observed upon cooling. The twin boundary formation together with the modulation of the structure was imaged by high resolution STM in the martensite phase. Electronic properties were investigated by ultra-violet photoemission spectroscopy showing pronounced differences in the valence band spectra of two phases. Financial support

by the BMBF within MSM-Sens 13N10061 and 13N10062 is gratefully acknowledged.

MA 10.62 Tue 10:45 Poster A

In vitro study of iron-palladium ferromagnetic shape-memory alloy in simulated body fluid (SBF) — ●YANHONG MA, FLORIAN SZILLAT, and STEFAN G. MAYR — Leibniz-Institut fuer Oberflaechenmodifizierung, Translationszentrum fuer regenerative Medizin und Fakultae fuer Physik und Geowissenschaften der Universitaet Leipzig, Permoserstrasse 15, 04318 Leipzig

Ferromagnetic shape memory alloys are a special class of active materials. They exhibit large actuation strain in martensitic phase due to a magnetic field induced reorientation of twin variants. For their biomedical applications, the biocompatibility is very important, as e.g. indicated by simulated body fluid (SBF) test. In the present study we focus on biocompatibility of Fe₇₀Pd₃₀ thin films. The surface morphologies and composition of the samples were studied by scanning electron microscopy equipped with energy dispersive X-ray spectroscopy. Analysis of the thin films crystalline structure was performed by X-ray diffraction. The elemental concentrations in SBF were measured after the samples were removed, using inductively coupled plasma optical emission spectroscopy. SBF experiments show that when the samples were immersed into the solution for 48 hours, some changes on the elemental concentration in SBF occurred. The Fe concentration in the as prepared SBF was about 0.002 mg/ml and no Pd was detected. After the sample was soaked into the solution for two days, concentrations of 0.028 mg/ml(Fe) and <0.001 mg/ml (Pd), respectively, were determined. This indicates, that some Fe moved into the solution from the film while the concentration of Pd did not change during the test.

MA 10.63 Tue 10:45 Poster A

Origin of the tetragonal distortion in Fe-Pd shape memory alloys — ●INGO OPAHLE¹, KLAUS KOEPERNIK², ULRIKE NITZSCHE², and MANUEL RICHTER² — ¹Institut für Theoretische Physik, Universität Frankfurt, 60438 Frankfurt/Main, Germany — ²IFW Dresden, P.O.B. 270016, D-01171 Dresden, Germany

Magnetic shape memory alloys (MSMA) have attracted considerable attention as materials for actuator and sensor applications, due to large magnetically induced strains of up to 10%. A promising MSMA is disordered Fe₇₀Pd₃₀ with an induced strain of about 6% and a relatively high blocking stress.

We have calculated the electronic structure of disordered Fe-Pd alloys [1] in the framework of density functional theory using the full potential local orbital (FPLO) code. The origin of the tetragonal distortion in these completely disordered alloys is found to be a Jahn-Teller like effect, which allows the system to reduce its band energy in a narrow composition range. In this composition range, the energy landscape along the Bain path is found to be flat, in agreement with a large tunability of strain observed in epitaxial films, covering most of the Bain path from fcc to bcc [2]. On the basis of our results, we discuss the prospects for an optimization of the alloys' properties by adding third elements, including effects on the magneto-crystalline anisotropy energy.

[1] I. Opahle *et al.*, Appl. Phys. Lett. 94 (2009) 072508.

[2] J. Buschbeck *et al.*, Phys. Rev. Lett. 103 (2009) 216101.

MA 10.64 Tue 10:45 Poster A

Herstellung und magnetische Charakterisierung von Co-Nanopartikel auf ionenstrahlerodierten Siliziumsubstraten — ●MATTHIAS BUHL, MICHAEL KÖRNER, MONIKA FRITZSCHE, ULRICH WIESENHÜTTER, OSKAR LIECKE und JÜRGEN FASSBENDER — Forschungszentrum Dresden - Rossendorf e.V., Dresden, Deutschland

Co-Nanopartikel wurden auf den selbstorganisierten Ripplern ionenstrahlerodierter Si-Substrate mittels Molekularstrahlepitaxie deponiert. Im Rahmen der Untersuchung sind Substrattemperatur und nominelle Beschichtungsdicke gezielt variiert worden. Mit Hilfe der longitudinalen magneto-optischen Kerr-Effekt Magnetometrie wurde der Einfluss der Ripple-Oberfläche auf das magnetische Verhalten der Co-Partikel analysiert. Die Auswertung der Messergebnisse von normierter remanenter Kerr-Drehung θ_r/θ_s und Koerzitivfeldstärke H_c zeigt eine kleine uniaxiale magnetische Anisotropie. Die leichte Richtung der Magnetisierbarkeit liegt parallel zu den Ripple-Wellenfronten.

MA 10.65 Tue 10:45 Poster A

Characterization of bioinspired synthesized magnetic nanoparticles — ●ANNALENA WOLFF¹, KATRIN ECKSTÄDT¹, DIETER AKEMEIER¹, INGA ENNEN¹, IRINA DÜCK¹, KATRIN

WOLLSCHLÄGER², NORBERT SEWALD², and ANDREAS HÜTTEN¹
¹Department of Physics, University of Bielefeld, Germany —
²Department of Chemistry, University of Bielefeld, Germany

Size distribution, morphology and magnetization of nanoparticles are important properties in many applications. In this study Cobalt Ferrite nanocrystals were synthesized using a biomineralization protein containing 25 amino acids and oxidative coprecipitation of Co^{2+} and Fe^{2+} . An AGM was used for magnetization measurements. A FIB DualBeam System was used to examine the morphology and size distribution. Furthermore the morphology and size distribution of chemically produced CoAu nanoparticles was examined with the DualBeam System and the magnetization with an AGM. Previously GMR was successfully measured on CoRuNanoparticles structures. Now GMR was measured of a setup consisting of two gold contacts which are connected through a structured monolayer of CoAu nanoparticles. GMR was measured at room temperature and at low temperatures. Two point measurements and four point geometry measurements on single particle are planned.

MA 10.66 Tue 10:45 Poster A

MOKE investigation of ferromagnetic nanoparticles deposited on a W(110) surface — ●CHRISTIAN KLEINHANS¹, WOLFGANG ROSELLEN¹, VOLKER HÜCKELKAMP¹, FURKAN BULUT^{1,2}, JOACHIM BANSMANN², ARMIN KLEIBERT³, and MATHIAS GETZLAFF¹ — ¹Institute of Applied Physics, University of Düsseldorf, Germany — ²Department of Surface Chemistry, Ulm University, Germany — ³Swiss Light Source at the Paul Scherrer Institute, Villigen, Switzerland

Magnetic properties of supported 3d-metal nanoparticles, differing from the behaviour of bulk material, open the possibility of applications from a technological point of view. With a continuously working, UHV-compatible arc cluster ion source (ACIS), ferromagnetic nanoparticles have been produced and subsequently mass filtered using an electrostatic quadrupole-deflector-unit, ensuring sizes of 5 to 15 nm. The deposition of these preformed free particles onto a W(110)-substrate is performed under soft-landing conditions. Their size and shape is determined by means of STM and TEM. Applying a magnetic field in plane of the sample with variable angle, the magnetic behaviour of the nanoparticles is characterised using magneto-optical Kerr effect (MOKE). The influence of the angle and strength of the magnetic field on the magnetization is used to determine the nanoparticles' magnetic anisotropy and correlate this characteristic property with the respective structural behaviour.

MA 10.67 Tue 10:45 Poster A

Temperaturabhängige Magnetrelaxometrie an magnetischen Nanopartikeln aus Magnetit im Temperaturbereich von 4,2 K bis 320 K — ●MARKUS SCHIFFLER¹, MARKUS BÜTTNER¹, PETER WEBER¹, PAUL SEIDEL¹, CLAUS LANG², DIRK SCHÜLER² und MICHAEL RÖDER³ — ¹Friedrich-Schiller-Universität Jena, Institut für Festkörperphysik — ²Ludwig-Maximilians-Universität München, Bereich Mikrobiologie — ³INNOVENT e.V. Jena

Obwohl Magnetit das älteste bekannte magnetische Material und seit vielen Jahren Gegenstand intensiver Untersuchungen ist sind die Ursachen vieler Eigenschaften noch nicht abschließend geklärt. Es wurden magnetische Nanopartikel aus einkristallinem Magnetit, die vom Bakterium *Magnetospirillum gryphiswaldense* erzeugt worden sind, mit Hilfe der temperaturabhängigen Magnetrelaxometrie (TMRX) untersucht. Dabei wird das Signal der magnetischen Relaxation der Probe mit einem axialen SQUID-Gradiometer zweiter Ordnung (Arbeitstemperatur 4,2 K) detektiert. Die Proben temperatur kann dabei durch einen entsprechenden Antikryostat im Bereich von 4,2 K bis 320 K variiert werden. Bei der Untersuchung der Magnetitpartikel wurden Relaxationssignale in verschiedenen Temperaturbereichen und mit verschiedenen Ursachen gefunden. Die Néelrelaxation liefert einen Beitrag bei Temperaturen ab 300 K. Im Temperaturbereich des für Magnetit bekannten Verwey-Übergangs bei 110 K liegen ebenfalls signifikante Signale vor, deren Herkunft bei TMRX-Messungen erklärbar ist. Zusätzlich existieren Signale zwischen 4,2 K und 70 K, die auf eine Relaxation magnetischer Momente hindeuten.

MA 10.68 Tue 10:45 Poster A

Oxidation of multilayers of ligand stabilized magnetic cobalt nanoparticles — ●BRITTA VOGEL¹, AXEL DREYER^{1,2}, NADINE MILL¹, KATRIN ECKSTÄDT¹, ANNALENA WOLFF¹, DIETER AKEMEIER¹, ALEXANDER WEDDEMANN¹, ALEXANDER AUGE¹, SIMONE HERTH¹, and ANDREAS HÜTTEN¹ — ¹Department of Physics,

University of Bielefeld, D-33615 Bielefeld, Germany — ²Department of Chemistry, University of Bielefeld, D-33615 Bielefeld, Germany

Cobalt nanoparticles have been prepared with TOPO, subsequently a ligand exchange was carried out. Samples have been prepared by dropping particle solution on Si-wafer, which lead to samples which consist of multilayers partially. The samples were studied with respect to the 3D order to gain information about the influence of the ligand on the 3D structure of the particle array and the oxidation process in multilayered particles.

MA 10.69 Tue 10:45 Poster A

Interplay between magnetism, structure and chemical order in small CoPt clusters: Ab initio and model calculations — ●LUCILA JUÁREZ-REYES, JESUS DORANTES-DÁVILA, and GUSTAVO PASTOR — Institut für Theoretische Physik, Universität Kassel, Germany

The magnetic properties of small Co_NPt_M clusters ($N + M \leq 5$) are studied using a generalized gradient approximation to the density functional theory (DFT) and a self-consistent tight-binding (SCTB) model. First, we perform a systematic study of all possible different topological geometries, spin-moment configurations and chemical orders in the framework of the DFT. Second, by using the optimal ab initio structures we determine the spin moments, orbital moments and magnetic anisotropy energy within the SCTB method. The DFT calculations yield compact structures with particularly short bond lengths among the Co atoms ($d_{Co-Co} \simeq 2.2 - 2.4 \text{ \AA}$). Pt doping induces an important enhancement of the Co spin moments μ_{Co} which are about $0.25\mu_B$ larger than μ_{Co} in Co_N . This is mainly due to important charge transfers between the Co and Pt atoms. SCTB calculations show a 15–20 % orbital contribution to the total magnetic moment. Finally, a non trivial dependence of the MAE landscape on Pt concentration is observed.

MA 10.70 Tue 10:45 Poster A

First principles study of segregation and interface effects in magnetic CoRh nanoparticles — ●LUIS ENRIQUE DIAZ SANCHEZ, JESUS DORANTES DAVILA, and GUSTAVO PASTOR — Institut für Theoretische Physik, Universität Kassel, Heinrich Plett. Str. 40, 34132 Kassel, Germany

The magnetic properties for Co_xRh_{1-x} nanoparticles in the size range $N \simeq 50 - 250$ atoms are investigated in the framework of density functional theory for concentrations $x = 0.0, 0.25, 0.5, 0.75$, and 1.0. CoRh clusters are found to be magnetic with an average spin moment per Co atom that is larger than in macroscopic alloys with similar concentrations. Results are given for the local and average spin moments, charge distribution, and density of electronic states for different types of segregation (e.g., core-shell, wetting, and non-wetting), interface mixing, and random alloys. The theoretical findings are discussed by comparison with available experiments.

MA 10.71 Tue 10:45 Poster A

Magnetic properties of CoRh core shell nanoparticles — ●BJÖRN MÜNZING¹, KAI FAUTH¹, NABIL ATAMENA², DIANA CIUCULESCU², and CATHERINE AMIENS² — ¹Physikalisches Institut, Universität Würzburg, Am Hubland, 97074 Würzburg, Germany — ²LCC Toulouse, 205 rte. de Narbonne, 31077 Toulouse Cedex 04, France

We present an X-ray magnetic circular dichroism (XMCD) study of the magnetic properties of Co@Rh core-shell nanoparticles with a mean diameter of ≈ 1.8 nm, prepared by colloidal chemistry using organometallic precursors.

The local Co atomic magnetic moments in particles of different composition increase with increasing amount of Rh. This may be attributed to a decreasing influence of tetramethylpiperidine ligands on the 3d-metal when the particle surface is enriched with Rh. The magnetic response is essentially superparamagnetic ($T \geq 12$ K) and magnetic saturation is not attained in applied fields of up to 3 T for all compositions. The measurement of the magnetic circular dichroism on Rhodium reveals the ferromagnetic coupling of Co and Rh in these particles.

Additionally we find striking differences in magnetic coupling between the particles at short inter particle distance. This could be attributed to an effective antiferromagnetic coupling once the particle surfaces are significantly enriched with Rh.

MA 10.72 Tue 10:45 Poster A

Resistive switching in nanocolumnar manganite thin films structured with e-beam lithography — ●CHRISTIN KALKERT, MARKUS ESSELING, JON-OLAF KRISPONEIT, VASILY MOSHNYAGA, BERND DAMASCHKE, and KONRAD SAMWER — I. Phys. Institut, Georg-August-Universität Göttingen, Friedrich-Hund-Platz 1, 37077 Göttingen

Manganites show an intriguing variety of different behavior such as the colossal magnetoresistance, the colossal electroresistance and a resistive switching phenomenon. Changing the resistance as a function of external parameters such as a magnetic or electric field has the potential of creating non-volatile memory applications.

In this work we studied $\text{La}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$ thin films prepared by metal-organic aerosol deposition technique on Al_2O_3 substrates. The films show columnar nanostructure as determined from X-ray diffraction and TEM measurements. After macroscopic electronic and magnetic characterisation we structured the films to μm -sized bridges by means of electron beam lithography. The current voltage dependences measured at 5 K indicate tunneling mechanism of conductivity and show resistive switching between low and high resistive states. The discussion is based on local structural changes at the grain boundaries.

This work is supported by DFG via SFB 602, TP A2 and the Leibniz Program.

MA 10.73 Tue 10:45 Poster A

Magnetoresistance of thin film microstructures of the Heusler compounds Cu_2MnAl and Co_2MnSi — ●MOHAMED OBAIDA^{1,2}, DENISE ERB², KURT WESTERHOLT², and HARTMUT ZABEL² — ¹Institut für Experimentalphysik 4, Ruhr-Universität Bochum, 44780 Bochum — ²National Research Center, Tahrir Street-Dokki., 12311 Cairo., Egypt.

We study the magnetoresistance of thin films of the ferromagnetic Heusler compounds Cu_2MnAl and Co_2MnSi . The Heusler thin films are prepared by UHV magnetron sputtering and shaped into rectangular bars with a width between $1\ \mu\text{m}$ and $50\ \mu\text{m}$ by optical lithography. The magnetoresistance is measured in magnetic fields up to 4 T and for the orientation of the field parallel and perpendicular to the in-plane current. In the as-prepared state the Heusler alloy films are non-ferromagnetic and exhibit a very small magnetoresistance only. The magnetoresistance strongly increases when the ferromagnetism gradually develops after step by step thermal annealing at high temperatures and decreases again when the magnetic moment approaches its maximum value. The magnetoresistance is dominated by an isotropic spin disorder contribution; only in the state with the maximum magnetic moment an additional small anisotropic magnetoresistance (AMR) can be resolved.

MA 10.74 Tue 10:45 Poster A

Large photoconductivity of $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_{3-\delta}/\text{SrTiO}_3$ heterostructures — ●ELKE BEYREUTHER¹, ANDREAS THIESSEN¹, STEFAN GRAFSTRÖM¹, KATHRIN DÖRR², and LUKAS M. ENG¹ — ¹Institut für Angewandte Photophysik, Technische Universität Dresden, D-01062 Dresden — ²Institut für Metallische Werkstoffe, IFW Dresden, D-01171 Dresden

The electric resistivity of stoichiometric and oxygen-deficient epitaxial 10-nm-thick $\text{La}_{0.7}\text{Ca}_{0.3}\text{MnO}_3$ thin films on SrTiO_3 under photoexcitation has been investigated systematically. In contrast to the as-prepared film, the oxygen-deficient one exhibits a pronounced photoinduced decrease of the resistivity of up to five orders of magnitude at low temperatures.

A detailed analysis of the resistivity as a function of illumination intensity and wavelength (visible to ultraviolet range) is presented for the bare substrate as well as for the film/substrate heterostructure. The roles of carrier generation in the film and carrier injection from the substrate, which both contribute to the observed effects, are discussed.

MA 10.75 Tue 10:45 Poster A

X-Ray magnetic circular dichroism (XMCD) study of magnetite (Fe_3O_4) thin films on semiconducting substrates — ●DOMINIK KUFER, MARKUS PAUL, ANDREAS MÜLLER, CHRISTIAN PRAETORIUS, ANNEMARIE KÖHL, KAI FAUTH, MICHAEL SING, and RALPH CLAESSEN — Lehrstuhl für Experimentelle Physik 4, Universität Würzburg, Germany

Thin films of magnetite have attracted enormous research interest in recent years because of their electronic and magnetic properties. Bulk magnetite shows ferrimagnetic ordering with a theoretically predicted

magnetic moment of $4\mu_B$ per formula unit below a favorably high Curie temperature of 850 K. However, structural, electronic and magnetic properties of thin films depend on choice of substrate, deposition method, and various process parameters. We have investigated the magnetic properties of epitaxial Fe_3O_4 thin films on the technologically relevant semiconducting substrates ZnO and GaAs by means of XMCD. Thin films were deposited by oxygen-assisted MBE and characterized by LEED, XPS and XRD. XMCD measurements were performed on samples with film thicknesses ranging from 3 to 40 nm, grown both *ex situ* as well as *in situ* shortly before data acquisition in total electron yield (TEY) mode. Our XMCD results confirm rather reduced magnetic moments in comparison with Fe_3O_4 bulk values [1]. Sum rule evaluation leads to spin magnetic moments in the range of $0.7\text{--}1.0\mu_B$ per atom and nearly vanishing orbital moments for both substrates.

[1] A.Müller *et al.*, arXiv:0911.3572

MA 10.76 Tue 10:45 Poster A

Magnetic anisotropy of Zn-substituted magnetite studied by ferromagnetic resonance — ●THEMISTOKLIS SIDIROPOULOS, DEEPAK VENKATESHVARAN, ANDREAS BRANDLMAIER, MATTHIAS ALTHAMMER, MATTHIAS OPEL, RUDOLF GROSS, and SEBASTIAN T.B. GOENNENWEIN — Walther-Meiner-Institut, Bayerische Akademie der Wissenschaften, Garching, Germany

Ferromagnetic resonance (FMR) is a powerful technique for the investigation of the magnetic anisotropy in ferromagnetic thin films. Here, we use FMR to study the magnetic anisotropy of $\text{Zn}_x\text{Fe}_{3-x}\text{O}_4$, a derivative of Fe_3O_4 . We have grown coherently strained, epitaxial $\text{Zn}_x\text{Fe}_{3-x}\text{O}_4$ thin films on MgO (001) substrates using pulsed laser deposition, monitored by an *in situ* RHEED system. Two sets of $\text{Zn}_x\text{Fe}_{3-x}\text{O}_4$ films (with $x = 0, 0.1, 0.33, 0.5$ and 0.9) were deposited, one in pure Ar, the other in an Ar/O₂ (99:1) mixture. X-ray diffraction measurements indicate high crystallinity, as evident from a FWHM of 0.04° in the rocking curves for the $\text{Zn}_x\text{Fe}_{3-x}\text{O}_4$ (004) reflection. Previously, we demonstrated that $\text{Zn}_x\text{Fe}_{3-x}\text{O}_4$ shows an appreciable tunability in both its magnetic and transport properties, depending on the Zn concentration and the growth atmosphere [1]. In this study, we discuss the evolution of the magnetic anisotropy with Zn concentration, growth atmosphere and temperature.

This work is supported by the DFG within SPP 1285, GO 944/3, and by the cluster of excellence Nanosystems Initiative Munich (NIM).

[1] D. Venkateshvaran *et al.*, Phys. Rev. B **79**, 134405 (2009).

MA 10.77 Tue 10:45 Poster A

Field and temperature dependence of spin and heat transport in dimerized spin 1/2 chains. — ●STEPHAN LANGER¹, FABIAN HEIDRICH-MEISNER¹, RACHID DARRADI², and WOLFRAM BREINIG² — ¹Physics Department, Arnold Sommerfeld Center for Theoretical Physics, and Center for NanoScience, LMU München, Germany — ²Institute for Theoretical Physics, Technical University of Braunschweig, Germany

We study the spin and heat conductivity of dimerized spin 1/2 chains in homogeneous magnetic fields at finite temperatures. Tuning the strength of the dimerization this model connects the limit of weakly coupled dimers to the Heisenberg chain. Our goal is to understand the dependence of heat and spin transport on the magnetic field, the temperature and the strength of dimerization. At zero temperature the model undergoes a field induced quantum phase transition from a dimerized into a Luttinger liquid phase. We search for signs of this transition in the spin and heat conductivity. Using exact diagonalization we calculate the Drude weights, the frequency dependence of the conductivities and the corresponding integrated spectral weights.

A similar transition from a gapped into a Luttinger Liquid phase is observed in spin ladder materials that have a comparably small exchange coupling, allowing experimentalists to probe transport at finite temperatures and fields. This serves as an additional motivation of our study.

This work is supported by the Deutsche Forschungsgemeinschaft via FOR 912.

MA 10.78 Tue 10:45 Poster A

Magnetic and Structural Properties of $\text{La}_{1-x}\text{Th}_x\text{CrO}_3$ and $\text{LaCr}_{1-y}\text{Ti}_y\text{O}_3$ — ●P. REUVEKAMP¹, R. K. KREMER¹, and F. S. RAZAVI² — ¹Max Planck Institut fuer Festkoerperforschung, — ²Department of Physics, Brock University, St. Catharines, Ontario, L2S 3A1, Canada

The magnetic properties of ceramic samples of $\text{La}_{1-x}\text{Th}_x\text{CrO}_3$ and

LaCr_{1-y}Ti_yO₃ were investigated. In order to improve the chemical homogeneity and stoichiometry, the ceramic samples were prepared by the citrate-pyrolysis synthesis route. X-ray investigations of these samples revealed that all the phases maintained their orthorhombic structure, however with different mass densities. The substitution of Th for La does not have effect on the magnetic properties of LaCrO₃ with the Néel temperature remaining close to 290 K whereas, replacing Ti for Cr reduces the Néel temperature to a minimum of 237 K for $y = 0.2$.

MA 10.79 Tue 10:45 Poster A

Magneto-Optic Measurements of Magnetic Multilayers in Extreme Ultraviolet Range — •ROMAN ADAM, PATRIK GRÝCHTOL, STEFAN CRAMM, and CLAUS SCHNEIDER — Institute of Solid State Research IFF-9, Research Center Jülich, D-52425

We performed static and time-resolved magneto-optic measurements on Co/Si-wedge/Ni/Fe and NiFe/MgO/Co multilayers using resonant scattering of extreme ultraviolet (XUV) radiation tuned to the M absorption edges of cobalt (60.2 eV) and nickel (67.5 eV). By exploiting the linear magneto dichroic effect close to the Brewster angle a huge magnetic contrast of up to 80% from the top Co and 20 % from the buried NiFe layer upon magnetization reversal could be obtained. In order to map the magnitude of the dichroism, angular and energy dependent scans of the magnetic asymmetry were performed and compared with magneto-optical simulations. The magneto-optical response of a multilayer system to a magnetic pulse excitation results in element-specific oscillations in a frequency range of 3 to 6.5 GHz associated with magnetization dynamics of the individual Co and NiFe layers. Presented results demonstrate the feasibility of element-specific

magneto-dynamic studies in magnetic multilayers in XUV spectral range.

MA 10.80 Tue 10:45 Poster A

Investigation of depletion state of high temperature protective coatings — •IULIAN TELIBAN¹, CLAAS THEDE¹, STEFFEN CHEMNITZ¹, CHRISTOPH BECHTOLD¹, THOMAS HÜTTEL², KRASIMIR ALEKSANDROV³, WILLEM QUADAKKERS², MICHAEL SCHÜTZE³, and ECKHARD QUANDT¹ — ¹Christian-Albrechts-Universität zu Kiel — ²Forschungszentrum Jülich — ³DECHEMA, Frankfurt a.M.

In many industrial applications metallic and non-metallic protective coatings are applied to protect against oxidation, corrosion or physical degradation. To date, practical non-destructive methods for the measurement of the depletion state of the coating during the operation time do not exist. By integration of magnetic phases into the coating and measuring the magnitude of the magnetic properties important information about the coating's condition can be provided.

A new technique using frequency mixing is presented to investigate the thickness of the coatings based on their magnetic properties. The performance of the sensor was investigated using magnetic samples with defined properties and thicknesses (Fe₆₇Co₁₈B₁₄Si₁ multilayers), [1]. Common protective coatings consisting of a paramagnetic MCrAlY matrix in which the sensor phase (Cr, Fe) is embedded and new types of coatings based on Al_{1-x}Cr_xN ($x = 0.02 \div 0.07$) are analyzed with the new technique in different stages of usage (oxidation).

Founding by the DFG via the SPP 1299 is gratefully acknowledged.

[1] I. Teliban, C. Thede, S. Chemnitz, C. Bechtold, W. J. Quadakkers, M. Schütze, and E. Quandt, Rev. Sci. Instrum. 80, 115106 (2009).