O 8: Electronic Structure and Spin-Orbit Interaction I

Time: Monday 10:30–13:00

O 8.1 Mon 10:30 GER 38 Depending on how you look at it - (un)conventional spin topology in the unoccupied band structure of Bi/Ag(111) — •SUNE N. P. WISSING¹, ANKE B. SCHMIDT¹, CHRISTIAN R. AST², HOSSEIN MIRHOSSEINI³, JÜRGEN HENK⁴, and MARKUS DONATH¹ — ¹Westfälische Wilhelms-Universität Münster, Germany — ²Max-Planck-Institut für Festkörperforschung Stuttgart, Germany — ³Johannes Gutenberg-Universität Mainz, Germany — ⁴Martin-Luther-Universität Halle-Wittenberg, Germany

We report on the challenge to determine the spin of the electronic structure out of a spin-polarized (inverse) photoemission experiment. For this purpose, we present a study on the unoccupied electronic structure of Bi/Ag(111) with spin- and angle-resolved inverse photoemission. Above the Fermi level, we identify several states with distinct spin character.

We focus our attention on the two p_{xy} -derived surface states. For the downward dispersing $m_j = 1/2$ state, theoretical calculations [1] predict a complex spin topology, where the spin polarization changes sign at the band maximum. Our experimental findings, however, indicate a spin splitting compatible with the conventional Rashba model. To shed more light on this issue, we investigated the spin topology with the help of first-principles electronic-structure and photoemission calculations. We will discuss the dependence of the measured spin topology on the polarization of the emitted light and the symmetry of the involved electronic states.

[1] G. Bihlmayer et al., Phys. Rev. B 75, 195414 (2007)

O 8.2 Mon 10:45 GER 38

Spin-flip scattering in the surface bands of $BiAg_2/Ag(111)$ — •GUSTAV BIHLMAYER¹, LYDIA EL-KAREH², MATTHIAS BODE², and STEFAN BLÜGEL¹ — ¹Peter Grünberg Institut and Institute of Advanced Simulation, Forschungszentrum Jülich and JARA, D-52425 Jülich, Germany — ²Physikalisches Institut, Experimentelle Physik II, Universität Würzburg, Am Hubland, D-97074 Würzburg, Germany

Since its discovery, the surface alloy BiAg₂/Ag(111) has attracted considerable attention due to the 'giant Rashba' splitting in the occupied surface bands. Recently, also the unoccupied part of the spectrum was investigated by scanning tunneling microscopy. But, although theory predicted a rather complex spin-texture of these bands [1], the quasiparticle interference patterns seem compatible with a conventional Rashba-type spin-polarization of these bands [2]. Close examination of the spin- and orbital resolved bandstructures obtained by density functional theory show, that the orbital structure allows spinflip scattering processes that can reconcile experimental evidence with theoretical predictions. Our calculations and experiments show that this behavior is not only characteristic for the Bi-based surface alloy, also in the $PbAg_2/Ag(111)$ system these spin-flip scattering events are observed. The same mechanism also blocks quasiparticle interference in forward scattering, while other scattering events are explicitly forbidden by time-reversal symmetry.

[1] G. Bihlmayer et al., Phys. Rev. B 75, 195414 (2007)

[2] L. El-Kareh et al., Phys. Rev. Lett. 110, 176803 (2013)

O 8.3 Mon 11:00 GER 38

Rashba-split surface states of $(\sqrt{3} \times \sqrt{3})$ **Pb/Ag(111)** $R30^{\circ}$ – •LYDIA EL-KAREH¹, GUSTAV BIHLMAYER², ARNE BUCHTER³, HEN-DRIK BENTMANN³, FRIEDRICH REINERT³, STEFAN BLÜGEL², and MATTHIAS BODE¹ – ¹Physikalisches Institut, Experimentelle Physik II, Universität Würzburg, Am Hubland, D-97074 Würzburg, Germany – ²Peter Grünberg Institut and Institute of Advanced Simulation, Forschungszentrum Jülich and JARA, D-52425 Jülich, Germany – ³Physikalisches Institut, Experimentelle Physik VII, Universität Würzburg, Am Hubland, D-97074 Würzburg, Germany

We report on a combined low-temperature scanning tunneling spectroscopy (STS), angle-resolved photoemission spectroscopy (ARPES), and density functional theory (DFT) investigation of the $(\sqrt{3} \times \sqrt{3})R30^{\circ}$ Pb/Ag(111) surface alloy which provides a giant Rashbatype spin-splitting [1,2]. By means of STS and quantum interference mapping we determined the band onsets, splitting strengths, and dispersions for two Rashba-split bands. The unambiguous assignment of scattering vectors is achieved by comparison to ARPES measurements. The detailed analysis of the spin and orbital character of both bands

Location: GER 38

as obtained by DFT calculations allows to solve an apparent deviation between experimentally observed scattering events and the theoretically predicted spin polarization [3].

[1] D. Pacilé et al., Phys. Rev. B 73, 245429 (2006).

[2] G. Bihlmayer *et al.*, Phys. Rev. B **75**, 195414 (2007).

[3] L. El-Kareh *et al.*, Phys. Rev. Lett. **110**, 176803 (2013).

O 8.4 Mon 11:15 GER 38 **The Unoccupied Band Structure of Pb/Ag(111)** — •KATHARINA T. RITTER, SUNE N. P. WISSING, ANKE B. SCHMIDT, and MARKUS DONATH — Physikalisches Institut, Westfälische Wilhelms-Universität Münster, Germany

Surface alloys of heavy elements on noble metal fcc(111) surfaces are known to exhibit strongly Rashba-split band structures. Especially the surface alloys with $(\sqrt{3} \times \sqrt{3})R30^\circ$ reconstruction have been in the focus of theoretical and experimental reasearch. So far, most experimental data result from photoemission experiments and hence are limited to the occuppied electronic states.

Here, we perform spin- and angle-resolved inverse photoemission to access the unoccupied band structure of Pb/Ag(111). Above the Fermi level, we identify several states with distinct spin dependence. We determine their nature concerning symmetry, bulk vs. surface character, energy vs. momentum dispersion, and spin character. As we recently also investigated the related surface alloy Bi/Ag(111), we will compare the results of both systems and analyse systematic changes accompanying the reduction of the number of valence electrons of the adsorbate by one.

O 8.5 Mon 11:30 GER 38 Bulk and surface Rashba states in ferroelectric GeTe: combined experimental and theoretical SX-ARPES study — H. VOLFOVA¹, J. KREMPASKY², H. DILL², V. STROCOV², J. BRAUN¹, H. EBERT¹, K. HRICOVIN⁶, R. CALARCO³, R. BERTACCO⁴, S. PICOZZI⁵, and •JAN MINAR¹ — ¹LMU Munich, Munich, Germany — ²PSI, Villigen, Switzerland — ³PDI Berlin, Germany — ⁴Politecnico Milano, Italy — ⁵CNR-SPIN L'Aquila, Italy — ⁶Universite de Cergy-Pontoise, France

The recent theoretical investigations of Picozzi et al. [1] predicted a huge Rashba effect originating from bulk states in ferroelectric GeTe, which spin polarisation can be switched by reversing its ferroelectric polarisation. However, detailed experimental and theoretical studies of the electronic structure by means of the angle resolved photoemission (ARPES) are until now missing. Here we present a combined theoretical and experimental study of the electronic structure of GeTe investigated with the aid of the bulk sensitive soft X-ray (SX)-ARPES [2]. It will be shown that a proper description of the photoemission process is necessary to understand the experimental results. These effects are included in the one-step model of photoemission implemented in the SPR-KKR package [3], which presents clear evidence for the predicted bulk Rashba state. [1] Di Sante et al., Andvanced materials 25, 509 (2013) [2] A. Gray, J. Minar et al., Nat. mat. 10, 759 (2011) [3] H. Ebert et al., Rep. Prog. Phys. 74, 096501 (2011)

O 8.6 Mon 11:45 GER 38 Chiral magnetism of magnetic adatoms from Rashba electrons — •JUBA BOUAZIZ¹, MANUEL DOS SANTOS DIAS¹, ABDELHAMID ZIANE², MOULOUD BENAKKI², STEFAN BLÜGEL¹, and SAMIR LOUNIS¹ — ¹Peter Grünberg Institut and Institute for Advanced Simulation, Forschungszentrum Jülich and JARA, D-52425 Jülich, Germany — ²Laboratoire de Physique et Chimie Quantique, Faculté des Sciences, Université Mouloud Mammeri, 15000 Tizi-Ouzou, Algeria

We investigate chiral magnetic long-range interactions among adatoms mediated by surface states spin-splitted by spin-orbit coupling. Using the Rashba model, the tensor of exchange interactions is extracted wherein a two-ion anisotropy term is found besides the usual isotropic exchange interaction (J) and the Dzyaloshinskii-Moriya interaction (DM). The inter-adatom distance controls the strength of these terms which we exploit to design chiral magnetism in Fe nanotructures on Au(111) surface. In contrast to [1], we include without approximation the contribution of the integrable singularity observed at the extremum of the dispersion curve. When the magnetic moments are out-of-plane, we demonstrate within a simple approach that J and DM are respectively related to superpositions of the out-of-plane and in-plane components of the skyrmionic magnetic waves induced by the adatoms in the surrounding electron gas [2].

This work is supported by the HGF-YIG Programme VH-NG-717 (Functional Nanoscale Structure and Probe Simulation Laboratory).

H. Imamura et al. Phys. Rev. B 69, 121303 (2004)

[2] S. Lounis et al. Phys. Rev. Lett. 108, 207202 (2012)

O 8.7 Mon 12:00 GER 38

Quasiparticle spin-interference by scattering off magnetic atoms on metal surfaces with spin orbit coupling — •PHILIPP RÜSSMANN, PHIVOS MAVROPOULOS, NGUYEN H. LONG, DAVID S. G. BAUER, and STEFAN BLÜGEL — Peter Grünberg Institute and Institute for Advanced Simulation, Forschungszentrum Jülich and JARA, D-52425 Jülich, Germany

We present density-functional calculations of the quasiparticle interference at surfaces due to scattering off magnetic adatoms. Our focus is on 3d impurities on Au(111) where the spin-orbit coupling (SOC) causes a Rashba-type splitting of the surface state. The spin polarization of the quasiparticle waves shows a non-collinear texture because of SOC. We investigate the dependence of the polarization on the orientation of the impurity magnetic moment. We compare to previous model-based results [1] and discuss the relation to the scattering properties of the impurity, taking into account the non-zero probability of time-reversed transitions due to the magnetic moment. In our calculations we employ the KKR-Green function method for the electronic structure and scattering properties at defects [2]. We acknowledge financial support from the DFG (SPP-1666) and from the Virtual Institute Topological Insulators of the Helmholtz Association and computational support from the JARA-HPC Supercomputing Center at the RWTH Aachen. [1] S. Lounis, A. Bringer, and S. Blügel, Phys. Rev. Lett. 108, 207202 (2012).

[2] S. Heers, PhD Thesis, RWTH Aachen (2011); D.S.G. Bauer, PhD Thesis, RWTH Aachen (2013).

O 8.8 Mon 12:15 GER 38

Giant splitting of unoccupied surface resonant state on Tl/Si(111) — •SEBASTIAN D. STOLWIJK¹, KAZUYUKI SAKAMOTO², ANKE B. SCHMIDT¹, PETER KRÜGER³, and MARKUS DONATH¹ — ¹Physikalisches Institut, Westfälische Wilhelms-Universität Münster — ²Department of Nanomaterials Science, Chiba University, Chiba 263-8522, Japan — ³Institut für Festkörpertheorie, Westfälische Wilhelms-Universität Münster

The Tl/Si(111)-(1 × 1) surface features outstanding properties - a unique spin pattern in momentum space and an unoccupied surface state with giant spin splitting at the \bar{K} point [1,2]. In this contribution, we focus on the unoccupied surface electronic structure along the $\bar{\Gamma}\bar{M}$ direction. Spin- and angle-resolved inverse photoemission experiments with sensitivity to the in-plane and out-of-plane components of the spin polarization vector are conducted with the help of our recently developed **RO**tatable **S**pin-polarized **E**lectron source (ROSE). Along $\bar{\Gamma}\bar{M}$ only in-plane polarization is found. Moreover, we identify a spin-orbit-split surface resonant state, which exhibits a Rashba-type splitting. Remarkably, the size of the Rashba splitting is comparable to the giant splitting found for the Bi/Ag(111) surface [3]. [1] K. Sakamoto et al., Phys. Rev. Lett. **102**, 096805 (2009)

[2] S. D. Stolwijk et al., Phys. Rev. Lett. **111**, 176402 (2013)

[3] C. Ast et al., Phys. Rev. Lett. 98, 186807, (2007)

O 8.9 Mon 12:30 GER 38

Spin-split surface states in the unoccupied electronic structure of Tl/Ge(111)-(1x1) — •PHILIPP EICKHOLT¹, SEBASTIAN D. STOLWIJK¹, ANKE B. SCHMIDT¹, PETER KRÜGER², and MARKUS DONATH¹ — ¹Physikalisches Institut, Westfälische Wilhelms Universität, Münster, Germany — ²Institut für Festkörpertheorie, Westfälische Wilhelms Universität, Münster, Germany

The unoccupied electronic structure of Tl/Si(111)-(1x1) exhibits a unique spin-orbit-split surface state with rotating polarization vector and giant energy splitting at the \overline{K} point [1]. Here, we present spin- and angle-resolved inverse-photoemission results on the unoccupied electronic structure of the isoelectronic Tl/Ge(111)-(1x1) surface, which is expected to show similar properties [2]. In fact, along the $\overline{\Gamma K}$ direction, a similar spin-orbit-split surface state is found with comparable properties as observed on Tl/Si(111). Differences between the two surfaces can be seen along $\overline{\Gamma M}$, where a Rashba-type spinsplit surface state on the Tl/Ge(111) surface lies well within a band gap, while it is degenerate with the bulk bands on the Si substrate. Remarkably, our measurements feature a spin asymmetry directly at the \overline{M} point where spin degeneracy should prevail.

Sebastian D. Stolwijk et al., Phys. Rev. Lett. **111**, 176402 (2013)
Y. Ohtsubo et al., J.Phys.: Condens. Matter **24**, 092001 (2012)

O 8.10 Mon 12:45 GER 38 Hysteretic melting of a soliton lattice in a commensurate charge modulation — •TOBIAS MAUERER¹, PIN-JUI HSU¹, MATTHIAS VOGT¹, J.J. YANG², YOON SEOK OH³, S-W. CHEONG^{2,3}, MATTHIAS BODE¹, and WEIDA WU³ — ¹Physikalisches Institut, Experimentelle Physik II, Universität Würzburg, Am Hubland, D-97074 Würzburg, Germany — ²Laboratory for Pohang Emergent Materials and Department of Physics, Pohang University of Science and Technology, Pohang 790-784, Republic of Korea — ³Rutgers Center for Emergent Materials and Department of Physics and Astronomy, Rutgers University, Piscataway, New Jersey 08854, USA

We report on the observation of the irreversible transition of a commensurate charge modulation in IrTe₂ from transport and scanning tunneling microscopy (STM) studies. Below the transition ($T_{\rm C} \approx 275$ K on cooling) a q = 1/5 charge modulation was observed, which is consistent with previous studies [1,2]. Additional modulations [$q_n = (3n + 2)^{-1}$] appear below a second transition at $T_{\rm S} \approx 180$ K on cooling. The coexistence of various modulations persist up to $T_{\rm C}$ on warming. The atomic structures of charge modulations and the temperature-dependent STM studies suggest that 1/5 modulation is a periodic soliton lattice which partially melts below $T_{\rm S}$ on cooling. Our results provide compelling evidence that the ground state of IrTe₂ is a commensurate 1/6 charge modulation, which originates from periodic dimerization of Te atoms visualized by atomically resolved STM images.

J. J. Yang *et al.*, Phys. Rev. Lett. **108**, 116402 (2012).
S. Pyon *et al.*, J. Phys. Soc. Jap. **81**, 053701 (2012).